

Exxtra™ Performance Polyolefin CMU201

Polypropylene, Compounded (TPO)

Product Description

A specialty thermoplastic polyolefin resin designed for automotive interior covered applications such as retainers in which a good stiffness toughness balance is required.

General

Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	
Features	<ul style="list-style-type: none"> Balanced Stiffness/Toughness Good Creep Resistance 	<ul style="list-style-type: none"> Good Dimensional Stability Good Mold Release 	<ul style="list-style-type: none"> Low Warpage
Uses	<ul style="list-style-type: none"> Automotive Applications Automotive Interior Parts 	<ul style="list-style-type: none"> Automotive Interior Trim Automotive Under the Hood 	
Appearance	<ul style="list-style-type: none"> Black 		
Form(s)	<ul style="list-style-type: none"> Pellets 		
Processing Method	<ul style="list-style-type: none"> Injection Molding 		
Revision Date	<ul style="list-style-type: none"> 11/25/2014 		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15 g/10 min	15 g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	1.04 in ³ /10min	17.0 cm ³ /10min	ISO 1133
Density	1.05 g/cm ³	1.05 g/cm ³	ISO 1183

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at Yield	3630 psi	25.0 MPa	ISO 527-2/50
Tensile Stress at Break	2760 psi	19.0 MPa	ISO 527-2/50
Tensile Strain at Yield	3.0 %	3.0 %	ISO 527-2/50
Tensile Strain at Break	23 %	23 %	ISO 527-2/50
Tensile Modulus - Secant	341000 psi	2350 MPa	ISO 527-2

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Charpy Notched Impact Strength			ISO 179
-4°F (-20°C), Complete Break	1.4 ft·lb/in ²	2.9 kJ/m ²	
32°F (0°C), Complete Break	1.5 ft·lb/in ²	3.2 kJ/m ²	
73°F (23°C), Complete Break	2.2 ft·lb/in ²	4.7 kJ/m ²	

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Heat Deflection Temperature (1.80 MPa)	140 °F	60.0 °C	ISO 75-2/A

Legal Statement

This product is not intended for use in food contact application.

This product is not intended for use in medical applications and should not be used in any such applications.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

