

Exxtra™ Performance Polyolefin CNU012

Polypropylene, Compounded (TPO)

Product Description

A specialty thermoplastic polyolefin resin designed for injection molded automotive applications.

General

Availability ¹	▪ Africa & Middle East	▪ Europe
Features	▪ Balanced Stiffness/Toughness	▪ Good Impact Resistance
Uses	▪ Automotive Applications	▪ Automotive Interior Trim
	▪ Automotive Interior Parts	▪ Automotive Under the Hood
Appearance	▪ Black	
Form(s)	▪ Pellets	
Processing Method	▪ Injection Molding	
Revision Date	▪ 10/31/2014	

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16 g/10 min	16 g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	1.28 in ³ /10min	21.0 cm ³ /10min	ISO 1133
Density	0.915 g/cm ³	0.915 g/cm ³	ISO 1183

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at Yield	3380 psi	23.3 MPa	ISO 527-2/50
Tensile Stress at Break	2470 psi	17.0 MPa	ISO 527-2/50
Tensile Strain at Yield	5.1 %	5.1 %	ISO 527-2/50
Tensile Strain at Break	> 50 %	> 50 %	ISO 527-2/50
Tensile Modulus - Secant	180000 psi	1240 MPa	ISO 527-2

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Charpy Notched Impact Strength			ISO 179
-4°F (-20°C), Complete Break	2.4 ft·lb/in ²	5.0 kJ/m ²	
32°F (0°C), Complete Break	2.6 ft·lb/in ²	5.4 kJ/m ²	
73°F (23°C), Complete Break	4.5 ft·lb/in ²	9.5 kJ/m ²	

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Heat Deflection Temperature (1.80 MPa)	122 °F	50.0 °C	ISO 75-2/A

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

This product is not intended for use in food contact application.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

