

Santoprene™ 8221-55M300

Thermoplastic Vulcanizate

Product Description

A soft, colorable, UV resistant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material is designed for automotive interior applications requiring low fogging and good appearance. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- Neutral, easy coloring formulation.
- Recommended for applications requiring excellent ozone resistance.
- Used in sealing applications.
- Recommended for applications requiring excellent flex fatigue resistance.
- Designed for improved UV resistance.

General

Availability ¹	▪ Africa & Middle East ▪ Asia Pacific	▪ Europe ▪ Latin America	▪ North America
Applications	▪ Automotive - Grips	▪ Automotive - Interior	▪ Automotive - Interior Mat
Uses	▪ Automotive Applications	▪ Automotive Interior Parts	▪ Outdoor Applications
RoHS Compliance	▪ RoHS Compliant		
Automotive Specifications	▪ CHRYSLER MS-AR-100 AMV2-HF	▪ FORD WSS-M2D510-A5	▪ GM GMW15816 Type 4
Color	▪ Natural Color		
Form(s)	▪ Pellets		
Processing Method	▪ Injection Molding	▪ Multi Injection Molding	
Revision Date	▪ 02/06/2015		

Physical

	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.930	0.930	ASTM D792
Density	0.930 g/cm ³	0.930 g/cm ³	ISO 1183

Hardness

	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness			ISO 868
Shore A, 15 sec, 73°F (23°C)	52	52	

Elastomers

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100% - Across Flow (73°F (23°C))	218 psi	1.50 MPa	ASTM D412
Tensile Stress at 100% - Across Flow (73°F (23°C))	218 psi	1.50 MPa	ISO 37
Tensile Strength at Break - Across Flow (73°F (23°C))	580 psi	4.00 MPa	ASTM D412
Tensile Stress at Break - Across Flow (73°F (23°C))	580 psi	4.00 MPa	ISO 37
Elongation at Break - Across Flow (73°F (23°C))	350 %	350 %	ASTM D412
Tensile Strain at Break - Across Flow (73°F (23°C))	350 %	350 %	ISO 37

Injection

	Typical Value (English)	Typical Value (SI)
Drying Temperature	180 °F	82 °C
Drying Time	3.0 hr	3.0 hr

Injection Notes

Santoprene™ TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Injection Molding Guide.



Santoprene™ 8221-55M300

Thermoplastic Vulcanizate

Additional Information

Where applicable, test results based on fan gated, injection molded plaques.

Tensile strength, elongation and tensile stress are measured across the flow direction - ISO type 1, ASTM die C.

Not recommended for hot oil.

All products purchased directly from an ExxonMobil affiliate in Europe are REACH compliant. For products not imported into Europe by ExxonMobil, customers should assess their legal responsibilities under REACH.

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

For detailed Product Stewardship information, please contact Customer Service.

Processing Statement

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene™ TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC. For more information, please consult our Safety Data Sheet and Injection Molding Guide.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2019 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com