

Exceed™ 1327KD

Metallocene Polyethylene Resin

Product Description

Exceed 1327KD is a metallocene ethylene-hexene copolymer. It produces films which have high modulus whilst retaining good toughness. Additionally, Exceed 1327KD is fully formulated with slip and antiblock, giving a versatile ready-to-use polymer for applications such as form fill and seal.

General

Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific Europe
Additive	<ul style="list-style-type: none"> Antiblock: 750 ppm Slip: 1300 ppm Processing Aid: Yes Thermal Stabilizer: Yes
Applications	<ul style="list-style-type: none"> Bag in Box Barrier Food Packaging Blown Film Bread Bags Food packaging Form Fill And Seal Packaging General Packaging Industrial Packaging Multilayer Packaging Film Overwrap Film Packaging Films Premium Trash Bags Shrink Film Stand Up Pouches Trash Bags Zipper Bag
Revision Date	<ul style="list-style-type: none"> 12/01/2012

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.927 g/cm ³	0.927 g/cm ³	ExxonMobil Method
Melt Index (190°C/2.16 kg)	1.3 g/10 min	1.3 g/10 min	ASTM D1238
Peak Melting Temperature	253 °F	123 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1800 psi	13 MPa	ASTM D882
Tensile Strength at Yield TD	2000 psi	14 MPa	ASTM D882
Tensile Strength at Break MD	7500 psi	50 MPa	ASTM D882
Tensile Strength at Break TD	6400 psi	44 MPa	ASTM D882
Elongation at Break MD	570 %	570 %	ASTM D882
Elongation at Break TD	690 %	690 %	ASTM D882
Secant Modulus MD - 1% Secant	42000 psi	290 MPa	ASTM D882
Secant Modulus TD - 1% Secant	46000 psi	320 MPa	ASTM D882
Dart Drop Impact	140 g	140 g	ASTM D1709A
Elmendorf Tear Strength MD	180 g	180 g	ASTM D1922
Elmendorf Tear Strength TD	500 g	500 g	ASTM D1922

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	33	33	ASTM D2457
Haze	24 %	24 %	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (1 mil/25.4 micron) made from Exceed 1327KD on a 2.5 inch (63.5 mm) blown film line with a 2.5:1 blow-up ratio, a melt temperature of 399°F (204°C), a 60 mil (1.52 mm) die gap at a rate of 10 lbs/hr/in die circumference (1.79 kg/hr/cm).



Exceed™ 1327KD
Metallocene Polyethylene Resin**Notes**

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2015 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com

