

ExxonMobil™ LDPE LD 605BA

Low Density Polyethylene Resin

Product Description

LD 605BA is a general purpose LDPE grade, characterized by good stiffness and good toughness. It's easy processable.

General

Availability	• Africa & Middle East	• Europe	
Additive	• Antiblock: No	• Slip: No	• Thermal Stabilizer: No
Applications	• Compounding • Food packaging	• Houseware Articles • Injection Molding	• Masterbatch Base Resin • Rigid Medium Sized Molding
Revision Date	• 10/2007		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.924 g/cm ³	0.924 g/cm ³	ExxonMobil Method
Melt Index (190°C/2.16 kg)	6.5 g/10 min	6.5 g/10 min	ASTM D1238
Peak Melting Temperature	232 °F	111 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	199 °F	93.0 °C	ISO 306

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Modulus	31900 psi	220 MPa	ISO 527-2/1A/1
Tensile Stress at Break	1450 psi	10.0 MPa	ISO 527-2/1A/50
Tensile Strain at Break	120 %	120 %	ISO 527-2/1A/50
Shore Hardness (Shore D, 15 sec)	46	46	ISO 868

Processing Statement

The molded properties have been measured on 4 mm (157.5 mil) thick injection molded specimen, based on ISO 1872-2.

Legal Statement

LD 605BA can - in principle - be used in food contact applications in various EU Member States and in the USA (FDA). Migration or use limitations may apply. Please contact your ExxonMobil Chemical representative for more detailed information and/or actual compliance certification documents for the specific grade of interest.

ExxonMobil Polyethylene is not intended for use in medical applications.

Typical properties: these are not to be construed as specifications.

© 2009 Exxon Mobil Corporation. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly own or control. ExxonMobil, the ExxonMobil Chemical Emblem, the "Interlocking X" Device, Enable, Exceed, Exact, Exxco, Escorene, Escor, lotek, NTX, Polybilt, Paxon and Opterna are trademarks or service marks of Exxon Mobil Corporation.