

Speciality grades / Medical devices

Developmental product; MFR 17 g/10 min; Medical devices; Low viscosity; Easy release; Injection molding; Available in transparent colors only

Property	Test Condition	Unit	Standard	Value
Rheological properties				
Melt flow rate	300 °C / 1.2 kg	g/(10 min)	ASTM D 1238	17
Mold shrinkage, flow/cross to flow		in/in	ASTM D 955	0.006-0.008
Mechanical properties (23 °C/50 % r.h.)				
Tensile modulus	1 mm/min	lb/in ²	ASTM D 638	330000
Tensile stress at yield	-	lb/in ²	ASTM D 638	8700
Tensile elongation at yield	-	%	ASTM D 638	5.0
Tensile elongation at break	-	%	ASTM D 638	115
Tensile stress at break	-	lb/in ²	ASTM D 638	9425
Flexural modulus	-	lb/in ²	ASTM D 790	320000
Thermal properties				
Thermal conductivity		Btu*in/(h*ftz**°F)	ASTM C 177	1.39
Specific heat		Btu/(lb.*°F)	ASTM D 2766	0.28
Electrical properties (23 °C/50 % r.h.)				
Volume resistivity, Tinfoil electrodes		Ohm-m	ASTM D 257	1.0
Other properties (23 °C)				
Water absorption	73 °F; immersion to saturation	%	ASTM D 570	0.30
Water absorption	73 °F; immersion 24 h	%	ASTM D 570	0.12
Density		lb/in ³	ASTM D 792	0.043
Specific volume		in ³ /lb	ASTM D 792	23.1
Specific gravity		-	ASTM D 792	1.2

Disclaimer**Standard Disclaimer**

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee, and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

Developmental Product

Any product designated as a developmental product is not considered part of the Bayer Polymers line of standard commercial products. Complete commercialization and continued supply are not assured. The purchaser/user agrees that Bayer Polymers reserves the right to discontinue this product without prior notice.

Typical Properties

Property data is provided as general information only. Property values are approximate and are not part of the product specifications.

Health and Safety

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling Bayer products mentioned in this publication. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets (MSDS) and product labels. Consult your Bayer Polymers representative or contact the Bayer Product Safety and Regulatory Affairs Department in Pittsburgh, Pennsylvania. For materials that are not Bayer products, appropriate industrial hygiene and other safety precautions recommended by their manufacturer(s) must be followed.