



Makrolon 2407

General purpose grades / Low viscosity / High productivity Global grade; MFR 20 g/10 min; General purpose; Low viscosity; UV stabilized; Easy release; Injection molding; Available in transparent, translucent and opaque colors

ISO Shortname

ISO 7391-PC,MLR,49-18-9

Property	Test Condition	Unit	Standard	Value
Rheological properties				
Melt flow rate	300 °C / 1.2 kg	g/(10 min)	ASTM D 1238	20
Mold shrinkage, flow/cross to flow		in/in	ASTM D 955	0.005-0.007
Mechanical properties (23 °C/50 % r.h.)				
Tensile modulus	1 mm/min	lb/in ²	ASTM D 638	350000
Tensile stress at yield	-	lb/in ²	ASTM D 638	9400
Tensile elongation at yield	-	%	ASTM D 638	6.0
Tensile elongation at break	-	%	ASTM D 638	115
Tensile stress at break	-	lb/in ²	ASTM D 638	8700
Izod notched impact strength	73 °F, 0.125 in	ft-lb/in	ASTM D 256	14
Flexural modulus	-	lb/in ²	ASTM D 790	340000
Flexural stress at 5 % strain		lb/in ²	ASTM D 790	12000
Rockwell hardness		M Scale	ASTM D 785	75
Rockwell hardness		R Scale	ASTM D 785	120
Thermal properties				
Deflection temperature under load, Unannealed	264 psi; 0.250 in	°F	ASTM D 648	259
Deflection temperature under load, Unannealed	66 psi; 0.250 in	°F	ASTM D 648	273
Vicat softening temperature	50 N, 50 °C/h	°F	ASTM D 1525	291
Coefficient of linear thermal expansion, flow/cross-flow		in/in/°F	ASTM D 696	3.34E-05
UL94 Flame Class	Thickness tested: 1.5 mm	Class	UL 94	V-2
UL94 Flame Class	Thickness tested: 3.0 mm	Class	UL 94	HB
UL94 Flame Class	Thickness tested: 6.0 mm	Class	UL 94	HB
Oxygen index		%	ASTM D 2863	28
Thermal conductivity		Btu*in/(h*ftz*°F)	ASTM C 177	1.39
Specific heat		Btu/(lb.°F)	ASTM D 2766	0.28
Relative temperature index, mechanical with impact	Thickness tested: 1.5 mm	°C	UL 746 B	115
Relative temperature index, mechanical without impact	Thickness tested: 1.5 mm	°C	UL 746 B	125
Relative temperature index, electrical	Thickness tested: 1.5 mm	°C	UL 746 B	125
Electrical properties (23 °C/50 % r.h.)				
Dissipation factor, Tinfoil electrodes	60 Hz	-	ASTM D 150	0.0008
Dissipation factor, Tinfoil electrodes	1 MHz	-	ASTM D 150	0.01
Dielectric constant, Tinfoil electrodes	60 Hz	-	ASTM D 150	3.0
Dielectric constant, Tinfoil electrodes	1 MHz	-	ASTM D 150	2.9
Volume resistivity, Tinfoil electrodes		Ohm-m	ASTM D 257	1.0 E+14
Surface resistivity		Ohm	ASTM D 257	1.0 E+16
Dielectric strength	Short time under oil at 73 °F; 0.162 in	V/mil	ASTM D 149	810
Other properties (23 °C)				
Water absorption	73 °F; immersion to saturation	%	ASTM D 570	0.3
Water absorption	73 °F; immersion 24 h	%	ASTM D 570	0.12
Density		lb/in ³	ASTM D 792	0.043
Specific volume		in ³ /lb	ASTM D 792	23.1
Specific gravity		-	ASTM D 792	1.2
Material specific properties				
Refractive index		-	ASTM D 542	1.586
Luminous transmittance (clear transparent materials)	0.125 in	%	ASTM D 1003	88
Haze for transparent materials	0.125 in	%	ASTM D 1003	< 0.8





Makrolon 2407

Disclaimer

Standard Disclaimer

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee, and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

Typical Properties

Property data is provided as general information only. Property values are approximate and are not part of the product specifications.

Flammability

Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions.

Health and Safety

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling Bayer products mentioned in this publication. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets (MSDS) and product labels. Consult your Bayer Polymers representative or contact the Bayer Product Safety and Regulatory Affairs Department in Pittsburgh, Pennsylvania. For materials that are not Bayer products, appropriate industrial hygiene and other safety precautions recommended by their manufacturer(s) must be followed.

Publisher: Business Development Plastics

Bayer MaterialScience AG,

D-51368 Leverkusen,

www.bayermaterialscience.com

Page 2 from 2 pages

Makrolon®

ASTM Dat

