



COVESTRO DEUTSCHLAND AG [PC RESINS]

Chempark
Gebäude B207
Leverkusen, 51368 Germany



Makrolon: 6555 + (z)(f2)

Polycarbonate (PC), pellets

- (f2) - Subjected to one or more of the following tests: Ultraviolet Light, Water Exposure or Immersion in accordance with UL 746C, where the acceptability for outdoor use is to be determined by UL.
- (z) - Material designation and color code may be followed by up to three letters and/or three numbers (does not include grades which are separately recognized with above material designation and suffix)
- + - Material designations may be followed by a six digit numerical code denoting color.

可燃性	值	测试方法
UL 阻燃等级		UL 94
1.0 mm, ALL	V-2	IEC 60695-11-10, -20
1.5 mm, ALL	V-2	
3.0 mm, ALL	V-0	
6.0 mm, ALL	V-0	
灼热丝易燃指数		IEC 60695-2-12
1.5 mm	960 °C	
3.0 mm	960 °C	
6.0 mm	960 °C	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
1.0 mm	PLC 3	
1.5 mm	PLC 2	
3.0 mm	PLC 1	
6.0 mm	PLC 1	
高电弧燃烧指数(HAI)		UL 746A
1.0 mm	PLC 2	
1.5 mm	PLC 2	
3.0 mm	PLC 1	
6.0 mm	PLC 1	
相比耐漏电起痕指数(CTI)	PLC 3	UL 746A
介电强度	29 kV/mm	ASTM D149
高电压电弧起痕速率 (HVTR)	PLC 2	UL 746A
体积电阻率	1.0E+15 ohms-cm	ASTM D257 IEC 60093
耐电弧性	PLC 6	ASTM D495
热性能	值	测试方法
RTI Elec		UL 746B
1.0 mm	80.0 °C	
1.5 mm	125 °C	
3.0 mm	125 °C	
6.0 mm	125 °C	



热性能	值	测试方法
RTI Imp		UL 746B
1.0 mm	80.0 °C	
1.5 mm	115 °C	
3.0 mm	115 °C	
6.0 mm	115 °C	
RTI		UL 746B
1.0 mm	80.0 °C	
1.5 mm	125 °C	
3.0 mm	125 °C	
6.0 mm	125 °C	
物理性能	值	测试方法
Dimensional Change	0.0 %	ASTM D1042 ISO 2796
室外适用性	f2	UL 746C



UL 94 小规模测试数据与建筑材料、家具和有关内容不相关。ANSI/UL 94 小规模测试数据仅用于确定成品设备和装置的组
中所用塑料材料的易燃性，其中组合的可接受性由 UL 确定。

