



COVESTRO DEUTSCHLAND AG [PC RESINS]

Chempark
Gebäude B207
Leverkusen, 51368 Germany



Makrolon: 8035 + (z)(f2)

Polycarbonate (PC), pellets

- (f2) - Subjected to one or more of the following tests: Ultraviolet Light, Water Exposure or Immersion in accordance with UL 746C, where the acceptability for outdoor use is to be determined by UL.
- (z) - Material designation and color code may be followed by up to three letters and/or three numbers (does not include grades which are separately recognized with above material designation and suffix)
- + - Material designations may be followed by a six digit numerical code denoting color.

可燃性	值	测试方法
UL 阻燃等级		UL 94
1.5 mm, ALL	V-1	IEC 60695-11-10, -20
3.0 mm, ALL	V-1	
6.0 mm, ALL	V-1	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746
1.5 mm	PLC 5	
3.0 mm	PLC 4	
6.0 mm	PLC 4	
高电弧燃烧指数(HAI)		UL 746
1.5 mm	PLC 4	
3.0 mm	PLC 4	
6.0 mm	PLC 4	
介电强度	26 kV/mm	ASTM D149 IEC 60243-1
高电压电弧起痕速率 (HVTR)	PLC 4	UL 746
耐电弧性	PLC 7	ASTM D495
热性能	值	测试方法
RTI Elec		UL 746
1.5 mm	125 °C	
3.0 mm	125 °C	
6.0 mm	125 °C	
RTI Imp		UL 746
1.5 mm	115 °C	
3.0 mm	115 °C	
6.0 mm	115 °C	
RTI		UL 746
1.5 mm	125 °C	
3.0 mm	125 °C	
6.0 mm	125 °C	
物理性能	值	测试方法
Dimensional Stability	0.0 %	ASTM D1042 ISO 2796
室外适用性	f2	UL 746C

