

Makrolon® FU1007

Grades / Special grade for furniture applications

MVR (300 °C/1.2 kg) 9.0 cm³/10 min; special grade for furniture applications with demands regarding fire standards UNI 8456, 8457, 9174 and 9175; medium viscosity; UV stabilized; easy release; injection molding - melt temperature 280 - 320 °C; available in transparent, translucent and opaque colors

ISO Shortname

ISO 7391-PC,MLR,(,.)-09-9

Property	Test Condition	Unit	Standard	typical Value
Rheological properties				
C Melt volume-flow rate	300 °C/ 1.2 kg	cm³/10 min	ISO 1133	9.0
C Molding shrinkage, parallel	60x60x2 mm/ 500 bar	%	ISO 294-4	0.65
C Molding shrinkage, normal	60x60x2 mm/ 500 bar	%	ISO 294-4	0.7
Molding shrinkage, parallel/normal	Value range based on general practical experience	%	b.o. ISO 2577	0.6 - 0.8
Melt mass-flow rate	300 °C/ 1.2 kg	g/10 min	ISO 1133	10
Mechanical properties (23 °C/50 % r. h.)				
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2400
C Yield stress	50 mm/min	MPa	ISO 527-1,-2	67
C Yield strain	50 mm/min	%	ISO 527-1,-2	6.1
C Nominal strain at break	50 mm/min	%	ISO 527-1,-2	> 50
Stress at break	50 mm/min	MPa	ISO 527-1,-2	70
Strain at break	50 mm/min	%	b.o. ISO 527-1,-2	120
C Tensile creep modulus	1 h	MPa	ISO 899-1	2200
C Tensile creep modulus	1000 h	MPa	ISO 899-1	1900
Flexural modulus	2 mm/min	MPa	ISO 178	2400
Flexural strength	2 mm/min	MPa	ISO 178	98
Flexural strain at flexural strength	2 mm/min	%	ISO 178	7.0
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178	74
C Charpy impact strength	23 °C	kJ/m²	ISO 179-1eU	N
C Charpy impact strength	-30 °C	kJ/m²	ISO 179-1eU	N
Charpy notched impact strength	23 °C/ 3 mm	kJ/m²	ISO 7391/b.o. ISO 179-1eA	75P
Charpy notched impact strength	-30 °C/ 3 mm	kJ/m²	ISO 7391/b.o. ISO 179-1eA	14C
Izod notched impact strength	23 °C/ 3 mm	kJ/m²	ISO 7391/b.o. ISO 180-A	70P
C Puncture maximum force	23 °C	N	ISO 6603-2	5400
C Puncture maximum force	-30 °C	N	ISO 6603-2	6300
C Puncture energy	23 °C	J	ISO 6603-2	60
C Puncture energy	-30 °C	J	ISO 6603-2	65
Ball indentation hardness		N/mm²	ISO 2039-1	116

Makrolon® FU1007

Property	Test Condition	Unit	Standard	typical Value
Thermal properties				
C Glass transition temperature	10 °C/min	°C	ISO 11357-1,-2	143
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	124
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	136
C Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	144
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	145
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.65
C Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.65
C Oxygen index	Method A	%	ISO 4589-2	28
Burning behavior UNI 9177 (incl.9174; 8456; 8457)	4.0 mm	Class	UNI 9177	1
Burning behavior UNI 9177 (incl.9174; 8456; 8457)	6.0 mm	Class	UNI 9177	1
Thermal conductivity, cross-flow	23 °C; 50 % r. h.	W/(m·K)	ISO 8302	0.20
Resistance to heat (ball pressure test)		°C	IEC 60695-10-2	135
Relative temperature index (Tensile strength)	1.5 mm	°C	UL 746B	125
Relative temperature index (Tensile impact strength)	1.5 mm	°C	UL 746B	115
Relative temperature index (Electric strength)	1.5 mm	°C	UL 746B	125
Application of flame from small burner	Method K and F/ 2.0 mm	Class	DIN 53438-1,-3	K1, F1
Burning rate (US-FMVSS)	>=1.0 mm	mm/min	ISO 3795	passed
Flash ignition temperature		°C	ASTM D1929	480
Self ignition temperature		°C	ASTM D1929	550
Other properties (23 °C)				
C Water absorption (saturation value)	Water at 23 °C	%	ISO 62	0.30
C Water absorption (equilibrium value)	23 °C; 50 % r. h.	%	ISO 62	0.12
C Density		kg/m³	ISO 1183-1	1200
Material specific properties				
Refractive index	Procedure A	-	ISO 489	1.586
Haze for transparent materials	3 mm	%	ISO 14782	< 0.8
Luminous transmittance (clear transparent materials)	1 mm	%	ISO 13468-2	89
C Luminous transmittance (clear transparent materials)	2 mm	%	ISO 13468-2	89
Luminous transmittance (clear transparent materials)	3 mm	%	ISO 13468-2	88
Luminous transmittance (clear transparent materials)	4 mm	%	ISO 13468-2	87
Processing conditions for test specimens				
C Injection molding-Melt temperature		°C	ISO 294	300
C Injection molding-Mold temperature		°C	ISO 294	80
C Injection molding-Injection velocity		mm/s	ISO 294	200

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break