

# Makrolon® TC210

/ moderate thermal conductivity; MVR (300 °C/1.2 kg) 4.0 cm³/10 min; high viscosity; values based on lab or small scale production; injection molding - melt temperature 300°C; available in white only; electrical/electronic

ISO Shortname PC-TD40

| Property                                            | Test Condition                | Unit                | Standard         | typical Value |
|-----------------------------------------------------|-------------------------------|---------------------|------------------|---------------|
| <b>Rheological properties</b>                       |                               |                     |                  |               |
| Melt volume-flow rate                               | 300 °C/ 1.2 kg                | cm³/10 min          | ISO 1133         | 4             |
| Melt viscosity                                      | 1000 s <sup>-1</sup> / 280 °C | Pa·s                | b.o. ISO 11443-A | 300           |
| Melt viscosity                                      | 1000 s <sup>-1</sup> / 300 °C | Pa·s                | b.o. ISO 11443-A | 180           |
| C Molding shrinkage, normal                         | 60x60x2 mm                    | %                   | ISO 294-4        | 0.3 - 0.4     |
| <b>Mechanical properties (23 °C/50 % r. h.)</b>     |                               |                     |                  |               |
| C Tensile modulus                                   | 1 mm/min                      | MPa                 | ISO 527-1,-2     | 7800          |
| Yield stress                                        | 5 mm/min                      | MPa                 | ISO 527-1,-2     | 0             |
| Yield strain                                        | 5 mm/min                      | %                   | ISO 527-1,-2     | 0             |
| Nominal strain at break                             | 5 mm/min                      | %                   | ISO 527-1,-2     | 1.4           |
| C Stress at break                                   | 5 mm/min                      | MPa                 | ISO 527-1,-2     | 49            |
| Flexural modulus                                    | 2 mm/min                      | MPa                 | ISO 178          | 8700          |
| Flexural strength                                   | 2 mm/min                      | MPa                 | ISO 178          | 80            |
| Flexural strain at flexural strength                | 2 mm/min                      | %                   | ISO 178          | 1.5           |
| Flexural stress at 3.5 % strain                     | 2 mm/min                      | MPa                 | ISO 178          | 0             |
| C Charpy impact strength                            | 23 °C                         | kJ/m²               | ISO 179/1eU      | 12            |
| C Puncture impact properties - maximum force        | 23 °C                         | N                   | ISO 6603-2       | 600           |
| C Puncture energy                                   | 23 °C                         | J                   | ISO 6603-2       | 3             |
| Ball indentation hardness                           |                               | N/mm²               | ISO 2039-1       | 128           |
| <b>Thermal properties</b>                           |                               |                     |                  |               |
| C Temperature of deflection under load              | 1.80 MPa                      | °C                  | ISO 75-1,-2      | 136           |
| C Temperature of deflection under load              | 0.45 MPa                      | °C                  | ISO 75-1,-2      | 144           |
| C Vicat softening temperature                       | 50 N; 50 °C/h                 | °C                  | ISO 306          | 146           |
| C Coefficient of linear thermal expansion, parallel | 23 to 55 °C                   | 10 <sup>-4</sup> /K | ISO 11359-1,-2   | 0.3           |
| C Coefficient of linear thermal expansion, normal   | 23 to 55 °C                   | 10 <sup>-4</sup> /K | ISO 11359-1,-2   | 0.5           |
| C Burning behavior UL 94                            | 1.0 mm                        | Class               | UL 94            | HB            |
| Thermal conductivity, through-plane                 | 23 °C; 50 % r. h.             | W/(m·K)             | ASTM E1461       | 0.3           |
| Thermal conductivity, in-plane                      | 23 °C; 50 % r. h.             | W/(m·K)             | ASTM E1461       | 1.4           |
| Glow wire test (GWFI)                               | 1.5 mm                        | °C                  | IEC 60695-2-12   | 850           |
| Glow wire test (GWIT)                               | 1.5 mm                        | °C                  | IEC 60695-2-13   | 850           |
| <b>Electrical properties (23 °C/50 % r. h.)</b>     |                               |                     |                  |               |
| C Volume resistivity                                |                               | Ohm·m               | IEC 60093        | >=E+16        |
| C Surface resistivity                               |                               | Ohm                 | IEC 60093        | >=E+16        |
| C Electrical strength                               | 1 mm                          | kV/mm               | IEC 60243-1      | 40            |
| <b>Other properties (23 °C)</b>                     |                               |                     |                  |               |
| C Density                                           |                               | kg/m³               | ISO 1183-1       | 1560          |
| <b>Processing conditions for test specimens</b>     |                               |                     |                  |               |
| C Injection molding - Melt temperature              |                               | °C                  | ISO 294          | 300           |
| C Injection molding - Mold temperature              |                               | °C                  | ISO 294          | 90            |

# Makrolon® TC210

| Property                                            | Test Condition | Unit | Standard | typical Value |
|-----------------------------------------------------|----------------|------|----------|---------------|
| <b>Recommended processing and drying conditions</b> |                |      |          |               |
| Dry Air Drying Temperature                          |                | °C   | -        | 120           |
| Dry Air Drying Time                                 |                | h    | -        | 4             |

**C** These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break





# Makrolon® TC210

## Disclaimer

Information Impact properties

Impact properties: N = non-break, P = partial break, C = complete break

Typical value

These values are typical values only. Unless explicitly agreed in written form, the do not constitute a binding material specification or warranted values. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the property values given have been established on standardized test specimens at room temperature.

General

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. With respect to health, safety and environment precautions, the relevant Material Safety Data Sheets (MSDS) and product labels must be observed prior to working with our products.

Non Medical and non Food Contact Grade

This product is not designated for the manufacture of a pharmaceutical/medicinal product, medical device or of intermediate products for medical devices<sup>1</sup>). This product is also not registered for Covestro for the use in other specifically regulated applications, in particular applications requiring regulatory registration, approval or notification (e.g. including cosmetics, plant protection, food processing, food contact and others). If the intended use of the product is for the manufacture of a pharmaceutical, medical device or of intermediate products for medical devices or for other specifically regulated applications which may lead to a regulatory obligation of Covestro, Covestro must be contacted in advance to provide its agreement to sell such product for such purpose. Nonetheless, any determination as to whether a product is appropriate for use in a pharmaceutical, medical device or intermediate products for medical devices or for the use in other specifically regulated applications, must be made solely by the purchaser of the product without relying upon any representations by Covestro, irrespective of the existence of any regulatory obligation for the registration, approval or notification. 1) Please see the "Guidance on Use of Covestro Products in a Medical Application" document.

Recommended Processing and Drying Conditions

Barrel temperatures are valid for a standard 3-zone barrel. Temperature set-up for different barrel types may change according to configuration. Values for hold pressure as percentage of injection pressure may vary depending on, amongst others, part geometry, injection molding machine and injection mold. Drying conditions are for dry air dryers only. Drying times and drying temperatures may differ depending on valid dryer type. Further information is provided by your local Covestro support as well as in the following brochures: Injection Molding of High Quality Molded Parts - Drying; Determining the Dryness of Makrolon by TVI Test; The fundamentals of shrinkage in thermoplastics; Shrinkage and deformation of glass fiber reinforced thermoplastics [...]. <https://www.plastics.covestro.com/Library/Overview.aspx>

Covestro AG

Polycarbonates Business Unit

Kaiser-Wilhelm-Allee 60

51373 Leverkusen

Germany

[plastics@covestro.com](mailto:plastics@covestro.com)

[www.plastics.covestro.com](http://www.plastics.covestro.com)

Page 3 of 3 pages



on 12.02.2021