



Makrolon 6557

Flame retardant grades / Medium viscosity

Global grade; MFR 10 g/10 min; Flame retardant; UL 94 V-0/3.0 mm; Medium viscosity; UV stabilized; Easy release; Injection molding; Available in transparent, translucent and opaque colors

ISO Shortname

ISO 7391-PC,MFLR,61-09-9

Property	Test Condition	Unit	Standard	Value
Rheological properties				
C Melt volume-flow rate	300 °C; 1.2 kg	cm ³ /(10 min)	ISO 1133	9.5
Molding shrinkage, parallel/normal	Value range based on general practical experience	%	acc. ISO 2577	0.6 - 0.8
Melt mass-flow rate	300 °C; 1.2 kg	g/(10 min)	ISO 1133	10
Mechanical properties (23 °C/50 % r. h.)				
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2400
C Yield stress	50 mm/min	MPa	ISO 527-1,-2	67
C Yield strain	50 mm/min	%	ISO 527-1,-2	6.1
C Nominal strain at break	50 mm/min	%	ISO 527-1,-2	> 50
Stress at break	50 mm/min	MPa	ISO 527-1,-2	65
Strain at break	50 mm/min	%	acc. ISO 527-1,-2	115
C Tensile creep modulus	1 h	MPa	ISO 899-1	2200
C Tensile creep modulus	1000 h	MPa	ISO 899-1	1900
Flexural modulus	2 mm/min	MPa	ISO 178	2350
Flexural strength	2 mm/min	MPa	ISO 178	98
Flexural strain at flexural strength	2 mm/min	%	ISO 178	7.0
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178	74
C Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	N
C Charpy impact strength	-30 °C	kJ/m ²	ISO 179-1eU	N
Charpy notched impact strength	23 °C; 3 mm	kJ/m ²	acc. ISO 179-1eA	70P(C)
Charpy notched impact strength	-30 °C; 3 mm	kJ/m ²	acc. ISO 179-1eA	12C
Izod notched impact strength	23 °C; 3.2 mm	kJ/m ²	acc. ISO 180-A	80P(C)
Izod notched impact strength	-30 °C; 3.2 mm	kJ/m ²	acc. ISO 180-A	12C
C Puncture maximum force	23 °C	N	ISO 6603-2	5400
C Puncture maximum force	-30 °C	N	ISO 6603-2	6300
C Puncture energy	23 °C	J	ISO 6603-2	60
C Puncture energy	-30 °C	J	ISO 6603-2	65
Ball indentation hardness		N/mm ²	ISO 2039-1	115
Thermal properties				
C Glass transition temperature	10 °C/min	°C	ISO 11357-1,-2	145
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	123
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	136
C Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	143
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	144
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.65
C Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.65
C Burning behavior UL 94 (1.6 mm) [UL listed]	1.5 mm	Class	UL 94	V-2
C Burning behavior UL 94 [UL listed]	3.0 mm	Class	UL 94	V-0
Burning behavior UL 94 [UL listed]	0.75 mm	Class	UL 94	V-2
Burning behavior UL 94 [UL listed]	6.0 mm	Class	UL 94	V-0
C Oxygen index	Method A	%	ISO 4589-2	36
Thermal conductivity	23 °C	W/(m·K)	ISO 8302	0.20
Resistance to heat (ball pressure test)		°C	IEC 60335-1	134
Temperature index (Tensile strength)	20000 h; 1.5 mm	°C	IEC 60216-1	130
Halving interval (Tensile strength)	1.5 mm	°C	IEC 60216-1	5.3
Temperature index (Tensile impact strength)	20000 h; 1.5 mm	°C	IEC 60216-1	120
Halving interval (Tensile impact strength)	1.5 mm	°C	IEC 60216-1	7.0
Temperature index (Electric strength)	20000 h; 1.5 mm	°C	IEC 60216-1	135
Halving interval (Electric strength)	1.5 mm	°C	IEC 60216-1	6.9
Relative temperature index (Tensile strength) [UL listed]	1.5 mm	°C	UL 746B	125
Relative temperature index (Tensile impact strength) [UL listed]	1.5 mm	°C	UL 746B	115
Relative temperature index (Electric strength) [UL listed]	1.5 mm	°C	UL 746B	125
Glow wire test (GWI)	1.0 mm	°C	IEC 60695-2-12	900



Makrolon 6557

Property	Test Condition	Unit	Standard	Value
Glow wire test (GWFI)	1.5 mm	°C	IEC 60695-2-12	960
Glow wire test (GWFI)	2.0 mm	°C	IEC 60695-2-12	960
Glow wire test (GWFI)	3.0 mm	°C	IEC 60695-2-12	960
Glow wire test	1.5 mm	°C	acc. EDF HN60 E.02	750
Glow wire test	3.0 mm	°C	acc. EDF HN60 E.02	750
Application of flame from small burner	Method K and F; 2.0 mm	Class	DIN 53438-1,-3	K1, F1
Needle flame test	Method K; 1.5 mm	s	IEC 60695-2-2	60
Needle flame test	Method K; 2.0 mm	s	IEC 60695-2-2	120
Needle flame test	Method K; 3.0 mm	s	IEC 60695-2-2	120
Needle flame test	Method F; 1.5 mm	s	IEC 60695-2-2	120
Needle flame test	Method F; 2.0 mm	s	IEC 60695-2-2	120
Needle flame test	Method F; 3.0 mm	s	IEC 60695-2-2	120
Incandescent bar test		Rating	IEC 60707-BH	BH2/< 30 mm
Burning rate (US-FMVSS)	>=1.0 mm	mm/min	ISO 3795	passed
Flammability to CSTB	2 mm	Rating	NF P 92-501	M4
Flammability to CSTB	3 mm	Rating	NF P 92-501	M4
Flammability to CSTB	4 mm	Rating	NF P 92-501	M4
Flash ignition temperature	Procedure B	°C	ASTM D1929	450
Self ignition temperature	Procedure B	°C	ASTM D1929	530

Electrical properties (23 °C/50 % r. h.)

C Relative permittivity	100 Hz	-	IEC 60250	3.1
C Relative permittivity	1 MHz	-	IEC 60250	3.0
C Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	5
C Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	85
C Volume resistivity		Ohm·m	IEC 60093	1E14
C Surface resistivity		Ohm	IEC 60093	1E16
C Electric strength	1 mm	kV/mm	IEC 60243-1	33
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	225
Comparative tracking index CTI M	Solution B	Rating	IEC 60112	125
Electrolytic corrosion		Rating	IEC 60426	A1

Other properties (23 °C)

C Water absorption (Saturation value)	Water at 23 °C	%	ISO 62	0.30
C Water absorption (Equilibrium value)	23 °C; 50 % RH	%	ISO 62	0.12
C Density		kg/m³	ISO 1183	1200
Water permeation	23 °C; 85 % RH; 100 µm film	g/(m²·24 h)	ISO 15106-1	15
Gas permeation	Oxygen; 100 µm film	cm³/(m²·24 h·bar)	acc. ISO 2556	700
Gas permeation	Oxygen; 25.4 µm (1 mil) film	cm³/(m²·24 h·bar)	acc. ISO 2556	2760
Gas permeation	Nitrogen; 100 µm film	cm³/(m²·24 h·bar)	acc. ISO 2556	130
Gas permeation	Nitrogen; 25.4 µm (1 mil) film	cm³/(m²·24 h·bar)	acc. ISO 2556	510
Gas permeation	Carbon dioxide; 100 µm film	cm³/(m²·24 h·bar)	acc. ISO 2556	4300
Gas permeation	Carbon dioxide; 25.4 µm (1 mil) film	cm³/(m²·24 h·bar)	acc. ISO 2556	16900
Bulk density	Pellets	kg/m³	ISO 60	640

Material specific properties

C Viscosity number		cm³/g	ISO 1628-4	59
Refractive index	Procedure A	-	ISO 489	1.586
Luminous transmittance (clear transparent materials)	1 mm	%	ISO 13468-2	89
C Luminous transmittance (clear transparent materials)	2 mm	%	ISO 13468-2	89
Luminous transmittance (clear transparent materials)	3 mm	%	ISO 13468-2	88
Luminous transmittance (clear transparent materials)	4 mm	%	ISO 13468-2	87

Processing conditions for test specimens

C Injection molding-Melt temperature		°C	ISO 294	300
C Injection molding-Mold temperature		°C	ISO 294	80
C Injection molding-Injection velocity		mm/s	ISO 294	200