

Bayblend® FR3000 BBS306

FR grades / Non reinforced

(PC+ABS)-Blend; flame retardant; Vicat/B 120 temperature = 97 °C; UL recognition 94 V-1 (2.0 mm)

ISO Shortname

PC+ABS-FR(40)

Property	Test Condition	Unit	Standard	typical Value
Rheological properties				
C Melt volume-flow rate	240 °C/ 5 kg	cm ³ /10 min	ISO 1133	23
Melt viscosity	1000 s ⁻¹ / 260 °C	Pa·s	b.o. ISO 11443-A	150
Molding shrinkage, parallel	150x105x3 mm/ 240 °C / MT 80 °C	%	b.o. ISO 2577	0.5 - 0.7
Molding shrinkage, normal	150x105x3 mm/ 240 °C / MT 80 °C	%	b.o. ISO 2577	0.5 - 0.7
Mechanical properties (23 °C/50 % r. h.)				
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2600
C Yield stress	50 mm/min	MPa	ISO 527-1,-2	61
Strain at break	50 mm/min	%	b.o. ISO 527-1,-2	40
Izod notched impact strength	23 °C	kJ/m ²	ISO 180-A	30
Thermal properties				
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	83
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	94
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	97
C Burning behavior UL 94	2.0 mm	Class	UL 94	V-1
Electrical properties (23 °C/50 % r. h.)				
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	350
Other properties (23 °C)				
C Density		kg/m ³	ISO 1183-1	1170
Processing conditions for test specimens				
C Injection molding-Melt temperature		°C	ISO 294	240
C Injection molding-Mold temperature		°C	ISO 294	80
C Injection molding-Injection velocity		mm/s	ISO 294	240
Recommended Processing and Drying Conditions				
Melt Temperatures		°C	-	240 - 270
Standard Melt Temperature		°C	-	260
Barrel Temperatures - Rear		°C	-	220 - 230
Barrel Temperatures - Middle		°C	-	225 - 235
Barrel Temperatures - Front		°C	-	230 - 240
Barrel Temperatures - Nozzle		°C	-	255 - 265
Mold Temperatures		°C	-	60 - 80
Hold Pressure (% of injection pressure)		%	-	50 - 75
Plastic Back Pressure (specific)		bar	-	50 - 150
Peripheral Screw Speed		m/s	-	0.05 - 0.2
Shot-to-Cylinder Size		%	-	30 - 70
Dry Air Drying Temperature		°C	-	80
Dry Air Drying Time		h	-	4
Moisture Content max. (%)		%	-	<= 0,02
Vent Depth		mm	-	0.025 - 0.075

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break

