

Bayblend® FR3010 HF

FR grades / Non reinforced

(PC+ABS)-Blend; flame retardant; easy flowing; Vicat/B 120 temperature = 108 °C; UL recognition 94 V-0 at 1.5 mm; glow wire temperature (GWFI): 960 °C at 2.0 mm; optimized processability; good light stability

ISO Shortname

PC+ABS-FR(40)

Property	Test Condition	Unit	Standard	typical Value
Rheological properties				
Spiral flow length	260 °C/80°C/ 2 x 8 mm	mm	Bayer test	400
Melt volume-flow rate	240 °C/ 5 kg	cm³/10 min	ISO 1133	25
Molding shrinkage, parallel	150x105x3 mm/ 240 °C / MT 80 °C	%	b.o. ISO 2577	0.5 - 0.7
Molding shrinkage, normal	150x105x3 mm/ 240 °C / MT 80 °C	%	b.o. ISO 2577	0.5 - 0.7
Mechanical properties (23 °C/50 % r. h.)				
Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2600
Yield stress	50 mm/min	MPa	ISO 527-1,-2	60
Yield strain	50 mm/min	%	ISO 527-1,-2	4
Stress at break	50 mm/min	MPa	ISO 527-1,-2	50
Strain at break	50 mm/min	%	b.o. ISO 527-1,-2	> 50
Izod impact strength	23 °C	kJ/m²	ISO 180-U	N
Izod notched impact strength	23 °C	kJ/m²	ISO 180-A	35
Izod notched impact strength	-30 °C	kJ/m²	ISO 180-A	10
Thermal properties				
Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	90
Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	100
Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	106
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	108
Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.76
Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.8
Burning behavior UL 94 (1.5 mm) [UL recognition]	1.5 mm	Class	UL 94	V-0
Burning behavior UL 94-5V [UL recognition]	2.2 mm	Class	UL 94	5VB
Burning behavior UL 94-5V [UL recognition]	3.0 mm	Class	UL 94	5VA
Electrical properties (23 °C/50 % r. h.)				
Relative permittivity	100 Hz	-	IEC 60250	3.2
Relative permittivity	1 MHz	-	IEC 60250	3.1
Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	40
Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	70
Volume resistivity		Ohm·m	IEC 60093	1E14
Surface resistivity		Ohm	IEC 60093	1E16
Electrical strength	1 mm	kV/mm	IEC 60243-1	35
Comparative tracking index CTI	Solution A	Rating	IEC 60112	350
Other properties (23 °C)				
Water absorption (saturation value)	Water at 23 °C	%	ISO 62	0.5
Water absorption (equilibrium value)	23 °C; 50 % r. h.	%	ISO 62	0.2
Density		kg/m³	ISO 1183-1	1180
Processing conditions for test specimens				
Injection molding-Melt temperature		°C	ISO 294	240
Injection molding-Mold temperature		°C	ISO 294	80
Injection molding-Injection velocity		mm/s	ISO 294	240

Bayblend® FR3010 HF

Property	Test Condition	Unit	Standard	typical Value
Recommended Processing and Drying Conditions				
Melt Temperatures		°C	-	240 - 270
Standard Melt Temperature		°C	-	260
Barrel Temperatures - Rear		°C	-	220 - 230
Barrel Temperatures - Middle		°C	-	225 - 235
Barrel Temperatures - Front		°C	-	230 - 240
Barrel Temperatures - Nozzle		°C	-	255 - 265
Mold Temperatures		°C	-	60 - 90
Hold Pressure (% of injection pressure)		%	-	50 - 75
Plastic Back Pressure (specific)		bar	-	50 - 150
Peripheral Screw Speed		m/s	-	0.05 - 0.2
Shot-to-Cylinder Size		%	-	30 - 70
Dry Air Drying Temperature		°C	-	80
Dry Air Drying Time		h	-	4
Moisture Content max. (%)		%	-	<= 0,02
Vent Depth		mm	-	0.025 - 0.075

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break