



Bayhydrol® UH 2869

Characterization	Aliphatic, polyester-based, anionic polyurethane dispersion. Binder for waterborne, air-and oven-drying pigmented coatings.
Form supplied	approx. 50 % in water, milky white

Characteristic data*

Property	Value	Unit of measurement	Method
Non-volatile content (1g / 1h / 125 °C)	49 - 51	%	DIN EN ISO 3251
Viscosity at 23 °C, spindle L 2 / 30 rpm	40 - 600	mPa·s	M092-ISO 2555
pH-value	6.0 - 9.0		DIN ISO 976

*These values are provisional. Binding supply specifications will not be available until the final product data sheet is published.

Other data**

Property	Value	Unit of measurement	Method
Density at 20 °C	approx. 1.1	g/cm ³	DIN 51 757
Minimum film-forming temperature	approx. 5	°C	DIN ISO 2115

**These values provide general information.



Bayhydrol® UH 2869

Compatibility

Bayhydrol® UH2869 is generally compatible with acrylic dispersions as well as water-reducible polyesters, melamine resins and polyurefin resins.

Properties / Applications

Bayhydrol® UH2869 has outstanding adhesion property on various materials, fast drying property and water resistance.

When used in multi-layer system, pigmented primer with Bayhydrol® UH2869 is characterized with faster drying property, good adhesion property on the substrates, water resistance and recoat-ability on SB polyurethane clearcoats

Storage

- Storage in original sealed Covestro containers.
- Recommended storage temperature: 5 - 23 °C, temperatures higher than 30 °C should be avoided.
- Protect from direct sunlight, frost, heat and foreign material.

General information: The product is sensitive to frost. Freezing can damage the product irreversibly. Prolonged storage at higher temperatures may affect the product properties and possibly resulting in sedimentation or coagulation. Containers must be kept sealed and protected from direct sunlight as otherwise the evaporation of water will result in the formation of a non-redispersible polymer film. Contamination with certain bacteria, fungi or algae may render the product unusable.



Bayhydrol® UH 2869

Storage time

Covestro represents that, for a period of six months following the day of shipment as stated in the respective transport documents, the product will meet the specifications or values set forth in section "specifications or characteristic data" above, what ever is applicable, provided that the product is stored in full compliance with the storage conditions set forth in and referenced under section "storage" above and is otherwise handled appropriately. The lapse of the six months period does not necessarily mean that the product no longer meets specifications or the set values. However, prior to using said product, Covestro recommends to test such a product if it still meets the specifications or the set values. Covestro does not make any representation regarding the product after the lapse of the six months period and Covestro shall not be responsible or liable in any way for the product failing to meet specifications or the set values after the lapse of the six months period.

Labeling and statutory requirements

This product data sheet is only valid in conjunction with the latest edition of the corresponding Safety Data Sheet. Any updating of safety-relevant information – in accordance with statutory requirements – will only be reflected in the Safety Data Sheet, copies of which will be revised and distributed. Information relating to the current classification and labeling, applications and processing methods and further data relevant to safety can be found in the currently **valid Safety Data Sheet**.

Important

This is a Trial Product of which we do not yet have extensive experience. No guarantee can therefore be given regarding the behaviour of the product during processing or use.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

This product is not designated for the manufacture of a medical device or of intermediate products for medical devices¹). [This product is also not designated for other specifically regulated applications (e.g. including cosmetics, plant protection, fertilisers, plant strengtheners, food processing, food contact and others). If the intended use of the product is for the manufacture of a medical device or of intermediate products for medical devices or for other specifically regulated applications Covestro must be contacted in advance to provide its agreement to sell such product for such purpose.] Nonetheless, any determination as to whether a product is appropriate for use in a medical device or intermediate products for medical devices, for Food Contact products or cosmetic applications must be made solely by the purchaser of the product without relying upon any representations by Covestro.

1) Please see the "Guidance on Use of Covestro Products in a Medical Application" document.

Edition: January, 2018

Editor: Coatings, Adhesives & Specialties
Covestro Deutschland AG
Kaiser-Wilhelm-Allee 60
51373 Leverkusen, Germany
www.covestro.com

Contact:
CAS Single Point of Contact APAC
e-mail: [cas_spoc_apac@covestro.com](mailto:cav_spoc_apac@covestro.com)

page 3 of 3

Edition 2022-01-05

 **Bayhydrol®**

Product Dat



Places edition dated 2015-08-31