



Desmopan 2587A GMP

Extrusion- and injection molding grade; does not contain any anti-hydrolysis agent; This product is manufactured under Good Manufacturing Practice (GMP defined in Regulation (EC) No. 2023/2006) and is therefore limited suitability for use with food contact. Please refer our separate certificate at <http://www.tpu.covestro.com/en/Library/Certificates/Food-Contact.aspx>; Application; Blown films

ARES

性能	测试条件	单位	标准	数值
				drying annealed - according to specifications

机械性能

C 邵氏硬度 A	1s	-	DIN ISO 7619-1	86
C 邵氏硬度 D	1s	-	DIN ISO 7619-1	33
C 最终拉伸强度	200 mm/min	MPa	DIN 53504	47, 6
C 断裂应变	200 mm/min	%	DIN 53504	478
C 10% 应变时的应力	200 mm/min	MPa	DIN 53504	2, 5
C 50% 应变时的应力	200 mm/min	MPa	DIN 53504	5, 3
C 100% 应变时的应力	200 mm/min	MPa	DIN 53504	6, 7
C 300% 应变时的应力	200 mm/min	MPa	DIN 53504	22, 4
C 压缩率	24 h; 70 ° C	%	DIN ISO 815-1, Method A	40
C 压缩率	24 h; 70 ° C	%	DIN ISO 815-1, Method C	25
C 耐磨性		mm ³	ISO 4649 method A	30
C 回弹力		%	ISO 4662	40
C 撕裂强度	500 mm/min	kN/m	ISO 34-1	70

热性质

C 抗扭储能模量	-20 ° C	MPa	ISO 6721-2	41
C 抗扭储能模量	23 ° C	MPa	ISO 6721-2	12
C 抗扭储能模量	70 ° C	MPa	ISO 6721-2	7, 7

其他性能 (23 ° C)

C 密度		kg/m ³	ISO 1183-1	1200
------	--	-------------------	------------	------

建议成型工艺参数说明:

C 注塑-熔体温度	°C	-	210 - 230
C 注塑-模具温度	°C	-	20 - 40
C 挤出-熔体温度	°C	-	195 - 215
C Maximum drying temperature	°C	-	80

C 这些性能数据来源于 CAMPUS 塑料数据库并且依据 ISO 10350 标准的国际分类原则





Desmopan 2587A GMP

声明

Covestro AG
Business Unit Polyurethanes
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany
www.TPU.covestro.com
www.covestro.com

页 2 的 2 页



01.02.2022

