



Desmopan 89785A

		Grade for calandring; no yellowing under the action of UV light; very good low-temperature impact strength; high rebound resilience; improved microbial resistance; Improved hydrolysis resistance; Textile coating				
		ALET				
性能	测试条件	单位	标准	数值		
				drying annealed -		
				according		
				to specifications		

机械性能

C 邵氏硬度 A	1s	-	DIN ISO 7619-1		86	
C 压缩率	24 h; 70 ° C	%	DIN ISO 815-1, Method A		40	
C 压缩率	72 h; 23 ° C	%	DIN ISO 815-1		20	
C 耐磨性		mm ³	ISO 4649 method A		30	
C 回弹力		%	ISO 4662		65	
C 撕裂强度	500 mm/min	kN/m	ISO 34-1		75	

其他性能 (23 ° C)

C 密度		kg/m ³	ISO 1183-1			1080
------	--	-------------------	------------	--	--	------

建议成型工艺参数说明:

C 注塑-熔体温度		°C	-	200-220		
C 注塑-模具温度		°C	-			20-40
C 挤出-熔体温度		°C	-	190		

C 这些性能数据来源于 CAMPUS 塑料数据库并且依据 ISO 10350 标准的国际分类原则





Desmopan 89785A

声明

Covestro AG
Business Unit Polyurethanes
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany
www.TPU.covestro.com
www.covestro.com

页 2 的 2 页



11.03.2022

