



Desmopan 9386A

900 品级系列, 醚类 / 邵氏硬度 A 85 - 89

Extrusion- and injection molding grade; very good hydrolysis and microbial resistance; good low-temperature flexibility; complies with VDE 0282-10; very large processing window; Application: Cable sheathings; Hoses, non-reinforced; Profiles

ARET

性能	测试条件	单位	标准	数值
				drying annealed - according to specifications

机械性能

C 邵氏硬度 A	1s	-	DIN ISO 7619-1	86
C 邵氏硬度 D	1s	-	DIN ISO 7619-1	34
C 最终拉伸强度	200 mm/min	MPa	DIN 53504	38
C 断裂应变	200 mm/min	%	DIN 53504	650
C 10% 应变时的应力	200 mm/min	MPa	DIN 53504	1, 9
C 50% 应变时的应力	200 mm/min	MPa	DIN 53504	5, 2
C 100% 应变时的应力	200 mm/min	MPa	DIN 53504	6, 8
C 300% 应变时的应力	200 mm/min	MPa	DIN 53504	10, 9
C 压缩率	24 h; 70 ° C	%	DIN ISO 815-1, Method A	49
C 压缩率	72 h; 23 ° C	%	DIN ISO 815-1	28
C 压缩率	24 h; 70 ° C	%	DIN ISO 815-1, Method C	36
C 耐磨性		mm ³	ISO 4649 method A	84
C 回弹力		%	ISO 4662	45
C 撕裂强度	500 mm/min	kN/m	ISO 34-1	60

热性质

C 拉伸储能模量	-20 ° C	MPa	ISO 6721-1, -4	152
C 拉伸储能模量	20 ° C	MPa	ISO 6721-1, -4	48
C 拉伸储能模量	60 ° C	MPa	ISO 6721-1, -4	35

其他性能 (23 ° C)

C 密度		kg/m ³	ISO 1183-1	1110
------	--	-------------------	------------	------

建议成型工艺参数说明:

C 注塑-熔体温度		°C	-	205 - 225	
C 注塑-模具温度		°C	-		20 - 40
C 挤出-熔体温度		°C	-	180 - 210	
C Maximum drying temperature		°C	-		80

C 这些性能数据来源于 CAMPUS 塑料数据库并且依据 ISO 10350 标准的国际分类原则



Desmopan 9386A

声明

Covestro AG
Business Unit Polyurethanes
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany
www.TPU.covestro.com
www.covestro.com

页 2 的 2 页



11.03.2022

