



Desmopan DP 9095AU

900 grade series, ether / Shore hardness D 45 - 49

injection molding grade; with special UV stabilizers; very good hydrolysis and microbial resistance; good wear resistance; low warpage; short cycle times; Application; Ear-tags

ISO Shortname

Property	Test Condition	Unit	Standard	Value		
				drying	annealed	-
				according to specifications		
Mechanical properties (23 °C/50 % r. h.)						
C shore hardness, method A		-	ISO 868		96	
C shore hardness, method D		-	ISO 868		43	
C Ultimate tensile strength	200 mm/min	MPa	acc. ISO 527-1,-3		50	
C Elongation at break	200 mm/min	%	acc. ISO 527-1,-3		400	
C Stress at 100 % strain	200 mm/min	MPa	acc. ISO 527-1,-3		16	
C Stress at 300 % strain	200 mm/min	MPa	acc. ISO 527-1,-3		33	
C Compression set	24 h; 70 °C	%	ISO 815		77	
C Compression set	72 h; 23 °C	%	ISO 815		30	
C Abrasion resistance		mm³	ISO 4649		18	
Impact resilience		%	ISO 4662		33	
Tear propagation resistance	500 mm/min	kN/m	ISO 34-1		129	
Thermal properties						
Torsional storage modulus	-20 °C	MPa	ISO 6721-2		275	
Torsional storage modulus	23 °C	MPa	ISO 6721-2		40	
Torsional storage modulus	70 °C	MPa	ISO 6721-2		19	
Tensile storage modulus	-20 °C	MPa	ISO 6721-1,-4		790	
Tensile storage modulus	20 °C	MPa	ISO 6721-1,-4		161	
Tensile storage modulus	60 °C	MPa	ISO 6721-1,-4		82	
Other properties (23 °C)						
C Density		kg/m³	ISO 1183			1149
Molding conditions						
Injection molding-Melt temperature		°C	-	200 - 220		
Injection molding-Mold temperature		°C	-			20
Maximum drying temperature		°C	-			80

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.