



Desmopan DP 9659DU

900 grade series, ether / Shore hardness D 55 - 59

Extrusion- and injection molding grade; with special UV stabilizers; transparent up to 6 mm wall thickness; very good hydrolysis and microbial resistance; Application; Ski boot shells; Hoses, non-reinforced

ISO Shortname

Property	Test Condition	Unit	Standard	Value drying annealed - according to specifications		
Mechanical properties (23 °C/50 % r. h.)						
C shore hardness, method A		-	ISO 868		97	
C shore hardness, method D		-	ISO 868		59	
C Ultimate tensile strength	200 mm/min	MPa	acc. ISO 527-1,-3		60	
C Elongation at break	200 mm/min	%	acc. ISO 527-1,-3		370	
C Stress at 100 % strain	200 mm/min	MPa	acc. ISO 527-1,-3		24	
C Stress at 300 % strain	200 mm/min	MPa	acc. ISO 527-1,-3		46	
C Compression set	24 h; 70 °C	%	ISO 815		82	
C Compression set	72 h; 23 °C	%	ISO 815		37	
C Abrasion resistance		mm³	ISO 4649		20	
Impact resilience		%	ISO 4662		29	
Tear propagation resistance	500 mm/min	kN/m	ISO 34-1		89	
Thermal properties						
Torsional storage modulus	-20 °C	MPa	ISO 6721-2		1370	
Torsional storage modulus	23 °C	MPa	ISO 6721-2		267	
Torsional storage modulus	70 °C	MPa	ISO 6721-2		75	
Other properties (23 °C)						
C Density		kg/m³	ISO 1183			1160
Molding conditions						
Injection molding-Melt temperature		°C	-	220 - 235		
Injection molding-Mold temperature		°C	-			40 - 60
Extrusion-Melt temperature		°C	-	205 -235		
Maximum drying temperature		°C	-			110

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.