



# Texin® 250DE

## Characterization

Texin 250DE resin is an aromatic polyester-based thermoplastic polyurethane with a Shore hardness of approximately 50D. It is processed primarily by extrusion and blow molding but can also be used for injection molding.

## Properties / Applications

Texin 250DE resin is characterized by a low gel content, good clarity, good abrasion resistance, and very good chemical resistance to oils, solvents, and other nonaqueous solutions. Texin 250DE natural color resin complies with FDA food-contact regulations 21 CFR 177.1680 (Polyurethane Resins) and 177.2600 (Rubber Articles Intended for Repeated Use), subject to the limitations of these and any other applicable regulations. A major feature of Texin 250DE resin is its wide processing window, which allows for ease of film and sheet production. Typical applications include belting, hose, cable jackets, hose jackets, athletic soles, film, tubing, and extruded profiles. As with any product, use of Texin 250DE resin in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

## Storage, Drying and Regrind Usage

Texin thermoplastic polyurethane resins are hygroscopic and will absorb ambient moisture. The resins should remain in their sealed containers and stored in a dry area. Storage temperatures should not exceed 86°F (30°C). Unused resin from opened containers, or reground material that is not to be used immediately, should also be stored in sealed containers under cool and dry conditions.

Prior to processing, Texin 250DE resin must be thoroughly dried for a minimum of 4 hours in a desiccant dehumidifying hopper dryer to a moisture content of less than 0.03%. Hopper inlet air temperature should be 200-220°F (93-104°C), the inlet air dew point should be -20°F (-29°C) or lower.

Where end-use requirements permit, up to 20% Texin resin regrind may be used with virgin material. Regrind material must be generated from properly molded/extruded parts, sprues, runners, trimmings, and/or films. Degraded or discolored material may not be used for regrind. All regrind material must be free of contamination and thoroughly blended with virgin material prior to drying and processing. Finished parts containing regrind must be tested to ensure that end-use requirements are fully met.

The use of regrind material should be avoided entirely in those applications where resin properties equivalent to virgin material are required, including but not limited to color quality, impact strength, resin purity and/or load-bearing performance.



Product Dat





# Texin® 250DE

## Injection Molding, Extrusion and Blow Molding Conditions

Typical starting conditions for injection molding, extrusion and blow molding are noted below. Actual processing conditions will depend on machine size, mold design, material residence time, shot size, part geometry, etc.

### Typical Injection Molding Conditions

Barrel Temperature: Rear	400°–420°F (204°–216°C)
Barrel Temperature: Middle	405°–425°F (207°–218°C)
Barrel Temperature: Front	405°–425°F (207°–218°C)
Barrel Temperature: Nozzle	410°–430°F (215°–221°C)
Melt Temperature	410°–430°F (215°–221°C)
Mold Temperature	70°–110°F (21°–43°C)
Injection Pressure	10,000 - 15,000 psi
Hold Pressure	60 - 80% of Injection Pressure
Back Pressure	800 psi max.
Screw Speed	40 - 80 rpm
Injection Speed	Slow to Moderate
Cushion	1/8 in max

### Extrusion and Blow Molding Profile

#### Typical Temperature Profile for Extrusion and Blow Molding

Rear (Feed)	390° - 410°F (199° - 210°C)
Middle (Transition)	400° - 420°F (204° - 216°C)
Front (Meter)	400° - 420°F (204° - 216°C)
Die	400° - 420°F (204° - 216°C)
Melt	400° - 420°F (204° - 216°C)



Product Data





# Texin® 250DE

## Typical Properties\* for Natural Resin

Property	ASTM Test Method (Other)	Texin 250DE Resin U.S. Units	Texin 250DE Resin S.I. Units
<b>General</b>			
Specific Gravity	D 792 (ISO 1183)	1.22	1.22
Shore Hardness	D 2240 (ISO 868)	95A/50D	95A/50D
Taber Abrasion: H-18, 1,000-g Load, 1,000 Cycles	D 3489 (ISO 4649)	70 mg Loss	70 mg Loss
Bayshore Resilience	D 2632	25%	25%
Mold Shrinkage, 100-mil thickness	D 955 (ISO 2577)		
Flow Direction		0.008 in/in (mm/mm)	0.008 in/in (mm/mm)
Cross-Flow Direction		0.008 in/in (mm/mm)	0.008 in/in (mm/mm)
<b>Mechanical</b>			
Tensile Strength	D 412 (ISO 37)	6,700 lb/in <sup>2</sup>	46.2 MPa
Tensile Stress at 100% Elongation	D 412 (ISO 37)	1,700 lb/in <sup>2</sup>	11.7 MPa
Tensile Stress at 300% Elongation	D 412 (ISO 37)	4,600 lb/in <sup>2</sup>	31.7 MPa
Ultimate Elongation	D 412 (ISO 37)	400%	400%
Flexural Modulus: 158°F (70°C) 73°F (23°C)	D 790 (ISO 178)	5,200 lb/in <sup>2</sup> 12,100 lb/in <sup>2</sup>	36 MPa 83 MPa
Tear Strength, Die C	D 624 (ISO 34)	775 lbf/in	136 kN/m
Compression Set (postcured): <sup>a</sup> 22 Hours at 158°F (70°C) 22 Hours at 73°F (23°C)	D 395-B (ISO 815)	35% 15%	35% 15%
<b>Thermal</b>			
Glass Transition Temperature (T <sub>g</sub> )	(DMA) <sup>b</sup>	-4°F	-20°C
Vicat Softening Temperature, Rate A (0.125-in, 10N, 0.833°C/min)	D 1525 (ISO 306)	239°F	115°C

\* These items are provided as general information only. They are approximate values and are not part of the product specifications.

<sup>a</sup> Postcured for 16 hours at 230°F (110°C), not postcuring will result in lower values.

<sup>b</sup> DMA – Dynamic Mechanical Analysis



Product Data





# Texin® 250DE

## Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling this product. Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., safety data sheets and product labels. For further information contact your Covestro LLC representative or the Product Safety and Regulatory Affairs Department in Pittsburgh, PA.

## Regulatory Compliance Information

Some of the end uses of the products described in this bulletin must comply with applicable regulations, such as the FDA, NSF, USDA, and CPSC. If you have any questions on the regulatory status of these products, contact your Covestro representative or Regulatory Affairs Manager in Pittsburgh, PA.

## Note

*The purchaser/user agrees that Covestro LLC reserves the right to discontinue this product without prior notice.*

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

 **Texin®**

Product Data

