



Texin 4215

/ Thermoplastic polyurethane/polycarbonate blend for injection molding and extrusion.

ISO Shortname

Property	Test Condition	Unit	Standard	Value
Rheological properties				
Mold shrinkage, flow/cross to flow	Value range based on general practical experience	in/in	ASTM D955	0.008
Mechanical properties (23 °C/50 % r. h.)				
Flexural modulus	73 °F	lb/in ²	ASTM D790	150000
Izod notched impact strength	73 °F, 0.125 in	ft·lb/in	ASTM D256	18
Izod notched impact strength	-22 °F; 0.125 in	ft·lb/in	ASTM D256	1.5
Shear strength		ft·lb/in ²	ASTM D732	7300
Tensile strength		lb/in ²	ASTM D412	6000
Ultimate elongation		%	ASTM D412	150
Tear strength, Die C		lbf/in	ASTM D624	950
Thermal properties				
Glass transition temperature	DMA=Dynamic Mechanical Analysis	°F	DMA	-31
Low-temperature brittle point		°F	ASTM D746	< -90
Deflection temperature under load	66 psi	°F	ASTM D648	227
Deflection temperature under load	264 psi	°F	ASTM D648	166
Vicat softening temperature	Rate A; 1 kg; 50 °C/h	°F	ASTM D1525	284
Coefficient of linear thermal expansion, flow/cross-flow		in/in/°F	ASTM D696	5
Other properties (23 °C)				
Specific gravity		-	ASTM D792	1.21
Shore hardness		D Scale	ASTM D2240	75
Bayshore resilience		%	ASTM D2632	52

