

Ajedium™ Films -- Halar® 500LC

ethylene chlorotrifluoroethylene copolymer

Halar® ECTFE is a semi-crystalline fluoropolymer with a chemical structure of a 1:1 alternating copolymer of ethylene and chlorotrifluoroethylene.

Halar® film is a strong, hard, tough, abrasion resistant film that retains its useful properties over a broad range of temperatures. Its low temperature properties, especially those related to impact, are particularly outstanding.

Halar® films have demonstrated excellent weathering properties and are extremely resistant to UV radiation and common industrial and environmental pollutants. The film also is an excellent barrier to water vapor at a wide range of temperatures. This lower permeability is a key advantage in applications where protection from water, oxygen, or other small gas molecules is required.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Low Viscosity	
Uses	• Aerospace Applications • Electrical/Electronic Applications	• Industrial Applications • Outdoor Applications
Appearance	• Clear/Transparent	

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.68		ASTM D792
Water Absorption (Equilibrium)	< 0.10	%	ASTM D570

Mechanical

	Typical Value	Unit	Test method
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.20		
vs. Itself - Static	0.20		
Taber Abrasion Resistance			
1000 Cycles, 500 g, CS-17 Wheel	5.00	mg	
Tear Resistance - MD	5.72		ASTM D1004

Films

	Typical Value	Unit	Test method
Film Thickness - Tested			
--	50	µm	
-- 1	50	µm	
-- 2	125	µm	
Secant Modulus			ASTM D882
MD	1550	MPa	
TD	1500	MPa	
Tensile Strength			ASTM D882
MD : Yield	34.5	MPa	
MD : Break	53.0	MPa	
TD : Break	50.0	MPa	

Ajedium™ Films -- Halar® 500LC

ethylene chlorotrifluoroethylene copolymer

Films	Typical Value	Unit	Test method
Tensile Elongation			ASTM D882
MD : Yield	6.0	%	
MD : Break	280	%	
TD : Break	280	%	
Dart Drop Impact	610	g	ASTM D1709B
Water Vapor Transmission Rate	1.6	g·mm/m ² /atm/24 hr	ASTM F1249
Free Shrinkage (200°C)	4.4	%	ASTM D2732
Area Factor	115	ft ² /lb/mil	
Tear Propagation Resistance - MD	> 6400	gf	ASTM D1922

Thermal	Typical Value	Unit	Test method
Brittleness Temperature	< -76.0	°C	ASTM D746A
Glass Transition Temperature	85.0	°C	DMA
Melting Temperature	242	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	222	°C	ASTM D3418
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696
Specific Heat (23°C)	962	J/kg/°C	ASTM D3418
Thermal Conductivity (40°C)	0.15	W/m/K	ASTM C177

Electrical	Typical Value	Unit	Test method
Volume Resistivity ³ (23°C)	5.5E+16	ohms·cm	ASTM D257
Dielectric Strength (23°C, 3.20 mm)	14	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	2.57		ASTM D150

Flammability	Typical Value	Unit	Test method
Oxygen Index	52	%	ASTM D2863

Additional Information

Standard Thicknesses and Widths

- Widths are available from 22" (559 mm) to 56" (1422 mm).
- Products with widths <22 inches or >56 inches are available upon request.
- Tolerances for widths are +/- 4mm.
- For Halar® film, the standard thicknesses are 8 microns (0.3 mil) to 1016 microns (40 mil).

Surface Finishes

- Standard surface finish is P/M (polished / matte).
- Custom finishes of P/P (polished / polished) and M/M (matte / matte) are available.

Packaging

- Film is supplied in a roll form of high quality, cardboard core of 3" (76mm) or 6" (152mm).
- PVC cores are available upon request in 3" and 6" sizes.

Labeling

- Products are labeled to comply with national and international standards.
- Labels include product grade, unique batch number, roll length, roll width, product thickness, and net weight.

Ajedium™ Films -- Halar® 500LC

ethylene chlorotrifluoroethylene copolymer

Notes

Typical properties: these are not to be construed as specifications.

¹ Impact properties

² Tear properties

³ 50% RH



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.