

Halar® 700 HC

ethylene chlorotrifluoroethylene copolymer

General

Material Status	• Commercial: Active
Availability	<ul style="list-style-type: none"> • Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Features	• Medium Viscosity
Forms	• Pellets
Processing Method	• Extrusion

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.70		ASTM D792
Melt Mass-Flow Rate (MFR) (275°C/2.16 kg)	7.0 to 10	g/10 min	ASTM D1238
Water Absorption (Equilibrium)	< 0.10	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus ¹ (23°C)	1320	MPa	ASTM D882
Tensile Strength ²			ISO 527-3
Yield, 23°C	28.5	MPa	
Break, 23°C	41.4	MPa	
Tensile Elongation ²			ISO 527-3
Yield, 23°C	5.0	%	
Break, 23°C	310	%	
Coefficient of Friction vs. Itself - Dynamic	0.20		ASTM D1894
Taber Abrasion Resistance 1000 Cycles, 500 g, CS-17 Wheel	16.5	mg	ASTM D4060

Films	Typical Value	Unit	Test method
Trouser Tear (23°C, 3.20 mm)	420.0	kN/m	DIN 53363

Hardness	Typical Value	Unit	Test method
Durometer Hardness (Shore D)	74		ASTM D2240

Thermal	Typical Value	Unit	Test method
Brittleness Temperature	< -50.0	°C	ASTM D746A
Glass Transition Temperature	70.0	°C	ASTM D4065
Melting Temperature	200	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	180	°C	ASTM D3418
Thermal Conductivity (23°C)	0.18	W/m/K	ASTM C177
Crystallization Heat	22.7	J/g	ASTM D3418
Heat of Fusion	24.0	J/g	ASTM D3418
Thermal Stability - 1% mass loss, N2	359	°C	TGA

Halar® 700 HC

ethylene chlorotrifluoroethylene copolymer

Electrical	Typical Value	Unit	Test method
Dielectric Strength (23°C, 3.20 mm)	14	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	2.57		ASTM D150

Flammability	Typical Value	Unit	Test method
Flame Rating	V-0		UL 94
Oxygen Index	> 52	%	ASTM D2863

Notes

Typical properties: these are not to be construed as specifications.

¹ 8.0 mm/min

² 500 mm/min



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.