

Tecnoflon® BR 9151 fluoroelastomer

Tecnoflon® BR 9151 is a new medium viscosity peroxide curable fluoroelastomer with a unique structure, patented by Solvay, that affords excellent resistance to aggressive oils, amine containing fluids, bases, and steam. Tecnoflon® BR 9151 exhibits superior resistance to a wide variety of chemicals (such as aggressive oils, amine containing fluids, bases and steam), coupled with excellent processability. Tecnoflon® BR 9151 can be cross-linked using organic peroxides in conjunction with a co-agent.

Some of the basic properties of Tecnoflon® BR 9151 are:

- Excellent chemical resistance to:
 - Bases
 - ATF fluids
 - Steam
 - Fluids containing amine additives
 - High PH packages
- Good mechanical properties
- Superior mold flow

- Lack of mold fouling
- Excellent mold release

Tecnoflon® BR 9151 can be used for compression, injection and transfer molding of shaft seals, valve seals, O-rings, gaskets or any item requiring superior chemical resistance.

Tecnoflon® BR 9151 can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers.

Finished goods may be produced by a variety of rubber processing methods. This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting.

Tecnoflon® BR 9151

fluoroelastomer

General

Material Status	• Commercial: Active	
Availability	• Europe	• North America
Features	<ul style="list-style-type: none"> • Base Resistant • Chemical Resistant • Crosslinkable • Good Flow • Good Mold Release 	<ul style="list-style-type: none"> • Good Processability • Medium Viscosity • Oil Resistant • Steam Resistant
Uses	<ul style="list-style-type: none"> • Belts/Belt Repair • Blending • Gaskets • Hose 	<ul style="list-style-type: none"> • Profiles • Seals • Sheet • Valves/Valve Parts
Appearance	• Translucent	
Forms	• Slab	
Processing Method	<ul style="list-style-type: none"> • Calendering • Compounding • Compression Molding 	<ul style="list-style-type: none"> • Extrusion • Injection Molding • Resin Transfer Molding

Physical

	Typical Value	Unit
Mooney Viscosity ¹ (ML 1+10, 121°C)	40	MU
Fluorine Content ¹	65	%

Notes

Typical properties: these are not to be construed as specifications.

¹ Raw polymer