

# Tecnoflon® FOR 60K

### fluoroelastomer

TECNOFLON® FOR 60K is a medium-low viscosity cure incorporated fluoroelastomers copolymer. This grade is designed to improve bonding in any application requiring adhesion to metal. In shaft seals or valve stem seals production, Tecnoflon® FOR 60K greatly reduces the reject rate due to adhesion problems.

Some of the basic properties of Tecnoflon® FOR 60K are:

- Superior bonding to metal
- Very good scorch safety
- Superior mold flow
- · Lack of mold fouling
- Excellent hot tear resistance

• Excellent mold release

Tecnoflon® FOR 60K can be used for injection, compression, and transfer moulding of gaskets and seals. The product can be mixed using typical fluoroelastomers compounding ingredients and mixing can be accomplished with two-roll mills or internal mixers.

The material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting. Finished goods can be produced by a variety of rubber processing methods.

## Tecnoflon® FOR 60K

### fluoroelastomer

#### General

Material Status	<ul> <li>Commercial: Active</li> </ul>	
Availability	• Europe	North America
Features	<ul><li>Bondability</li><li>Copolymer</li><li>Good Adhesion</li><li>Good Mold Release</li></ul>	<ul><li>Good Tear Strength</li><li>High Flow</li><li>Medium-low Viscosity</li></ul>
Uses	<ul><li>Adhesives</li><li>Blending</li><li>Bonding</li><li>Gaskets</li><li>Hose</li></ul>	<ul><li> Metal Bonding</li><li> Profiles</li><li> Seals</li><li> Sheet</li></ul>
Appearance	Off-White	
Forms	• Slab	
Processing Method	<ul><li>Calendering</li><li>Compounding</li><li>Compression Molding</li></ul>	<ul><li>Extrusion</li><li>Injection Molding</li><li>Resin Transfer Molding</li></ul>
Physical	Typical Value Unit	
Mooney Viscosity 1 (ML 1+10, 121°C)		30 MU

66 %

#### Notes

Typical properties: these are not to be construed as specifications.

Fluorine Content 1

<sup>&</sup>lt;sup>1</sup> Raw polymer