

## Tecnoflon® PL 455

### fluoroelastomer

TECNOFLON® PL 455 is a new generation low temperature peroxide curable low viscosity fluoroelastomer with 64% wt fluorine content. Tecnoflon® PL 455 exhibits excellent low temperature flexibility (TR10 = -30°C). Like all other Tecnoflon® peroxide curable grades, it exhibits excellent processability; moreover it needs very short post-curing cycles.

Some of the basic properties of Tecnoflon® PL 455 are:

- Excellent low temperature flexibility
- Low post cure
- Superior mold flow
- Lack of mold fouling

- Excellent mold release

Tecnoflon® PL 455 can be used for injection, injection-compression and transfer molding of O-rings, gaskets and seals. Tecnoflon® PL 455 can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers.

This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting. Finished goods may be produced by a variety of rubber processing methods.

# Tecnoflon® PL 455

## fluoroelastomer

### General

Material Status	• Commercial: Active	
Availability	• Europe	• North America
Features	• Fast Cure • Good Flow • Good Mold Release	• Good Processability • Low Temperature Flexibility • Low Viscosity
Uses	• Belts/Belt Repair • Blending • Gaskets • Hose	• Low Temperature Applications • Profiles • Seals • Sheet
Appearance	• Translucent	
Forms	• Slab	
Processing Method	• Calendering • Compounding • Compression Molding	• Extrusion • Injection Molding • Resin Transfer Molding

### Physical

#### Typical Value Unit

Mooney Viscosity <sup>1</sup> (ML 1+10, 121°C)	19	MU
Fluorine Content <sup>1</sup>	64	%

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Raw polymer