

Kalix® 2555

high performance polyamide

Kalix® 2555 is a bio-sourced, polyamide-based compound with 55% by weight glass reinforcement. This material is specifically formulated for high strength and stiffness applications where good impact resistance, outstanding dielectric properties, and excellent dimensional stability after molding are required. Its low viscosity and excellent flow properties make the material ideal for filling parts with

thin-walled sections such as those encountered in the mobile electronics industry.

- Natural: Kalix® 2555 NT 000
- Black: Kalix® 2555 BK 000

General

| | | |
|------------------------|--|---|
| Material Status | • Commercial: Active | |
| Availability | • Asia Pacific | |
| Filler / Reinforcement | • Glass Fiber, 55% Filler by Weight | |
| Features | <ul style="list-style-type: none"> • Fast Molding Cycle • Good Dimensional Stability • Good Electrical Properties • Good Impact Resistance • Good Surface Finish • High Flow | <ul style="list-style-type: none"> • High Stiffness • High Strength • Hot Water Moldability • Paintable • Platable |
| Uses | <ul style="list-style-type: none"> • Cell Phones • Electrical Parts | <ul style="list-style-type: none"> • Electrical/Electronic Applications • Thin-walled Parts |
| RoHS Compliance | • RoHS Compliant | |
| Appearance | • Black | • White |
| Forms | • Pellets | |
| Processing Method | • Injection Molding | • Water-Heated Mold Injection Molding |

Physical

| | Typical Value | Unit | Test method |
|--------------------------------|---------------|------|-----------------|
| Specific Gravity | 1.50 | | |
| Molding Shrinkage ¹ | | | Internal Method |
| Across Flow | 0.58 | % | |
| Flow | 0.17 | % | |
| Water Absorption (24 hr, 23°C) | 0.10 | % | ASTM D570 |

Mechanical

| | Typical Value | Unit | Test method |
|------------------------|---------------|------|-------------|
| Tensile Modulus | 15500 | MPa | ISO 527-2 |
| Tensile Stress | 205 | MPa | ISO 527-2 |
| Tensile Strain (Break) | 3.5 | % | ISO 527-2 |
| Flexural Modulus | 14000 | MPa | ISO 178 |
| Flexural Stress | 320 | MPa | ISO 178 |

Impact

| | Typical Value | Unit | Test method |
|--------------------------------|---------------|-------|-------------|
| Notched Izod Impact Strength | 18 | kJ/m² | ISO 180/1A |
| Unnotched Izod Impact Strength | 90 | kJ/m² | ISO 180 |

Kalix® 2555

high performance polyamide

| Thermal | Typical Value | Unit | Test method |
|--|---------------|------|-------------|
| Heat Deflection Temperature 1.8 MPa, Unannealed | 205 | °C | ISO 75-2/A |
| Electrical | Typical Value | Unit | Test method |
| Dielectric Constant ² (2.40 GHz) | 3.50 | | ASTM D2520 |
| Dissipation Factor ² (2.40 GHz) | 0.010 | | ASTM D2520 |
| Flammability | Typical Value | Unit | Test method |
| Flame Rating (0.75 mm, ALL) | HB | | UL 94 |

Additional Information

Typical values shown tested on Dry as Molded samples.

Standard Packaging and Labeling:

- Kalix® resin is packaged in foil lined, multiwall paper bags containing 25 kg (55 pounds) of material. Individual packages will be plainly marked with the product number, the color, the lot number, and the net weight.

| Injection | Typical Value | Unit |
|------------------------|---------------|------|
| Drying Temperature | 80 | °C |
| Drying Time | 4.0 to 12 | hr |
| Suggested Max Moisture | 0.090 | % |
| Rear Temperature | 265 to 300 | °C |
| Middle Temperature | 280 to 330 | °C |
| Front Temperature | 280 to 330 | °C |
| Processing (Melt) Temp | 280 to 330 | °C |
| Mold Temperature | 50 to 130 | °C |

Injection Notes

Storage:

- Kalix® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Kalix® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Kalix® processing guide.

Drying:

- Kalix® is supplied in sealed bags. It should be dried before molding because excessive moisture content will result in reduced mechanical properties and processing issues, such as excessive nozzle drooling, foaming and splay visible on the molded parts.
- Use of a desiccant dryer with -40°C dewpoint is strongly suggested to ensure Kalix® material has reached optimum moisture content before processing.

Injection Molding:

- Set injection pressure to give rapid injection. Adjust holding pressure to one-half injection pressure. Set hold time to maximize part weight. Transfer from injection to hold pressure at the screw position just before the part is completely filled.
- For light colors use lower melt temperature if possible. If operating in the 330°C melt temperature range, keep residence times below 5 minutes.
- Actual mold temperatures of 80°C or above are recommended to improve flow and part surface finish. The use of mold temperatures below 80°C is safe for mechanical properties but may result in higher necessary injection pressure and inferior surface finish.

Notes

Typical properties: these are not to be construed as specifications.

¹ Solvay Test Method. Shrink rates can vary with part design and processing conditions. Please consult a Solvay Technical Representative for more information.

² Method B

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.