

## Xydar® M-345

### liquid crystal polymer

Xydar® M-345 liquid crystal polymer (LCP) is a 45% mineral reinforced injection molding grade developed for electrical/electronic applications utilizing surface mount technology. The material can fill very thin walls over long flow lengths.

In addition to low warpage, it exhibits good strength and stiffness (even at elevated temperatures), low coefficient of

thermal expansion, high heat deflection temperature, inherent flame resistance and good chemical and weathering resistance.

- Natural: M-345 NT
- Black: M-345 BK

#### General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• North America
Filler / Reinforcement	• Mineral, 45% Filler by Weight	
Features	• Chemical Resistant • Flame Retardant • Good Moldability • Good Stiffness	• Good Strength • Low Warpage • Weather Resistant
RoHS Compliance	• Contact Manufacturer	
Appearance	• Black	• Natural Color
Forms	• Pellets	
Processing Method	• Injection Molding	

#### Physical

	Typical Value	Unit	Test method
Density	1.80	g/cm <sup>3</sup>	ISO 1183
Ash Content	45	%	

#### Mechanical

	Typical Value	Unit	Test method
Tensile Modulus - Chord <sup>1</sup>	8200	MPa	ISO 527-2
Tensile Stress (Break)	80.0	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Flexural Modulus - Chord <sup>1</sup>	9700	MPa	ISO 178
Flexural Strain at Break	3.0	%	ISO 178
Flexural Strength (Break)	87.0	MPa	ISO 178

#### Impact

	Typical Value	Unit	Test method
Charpy Notched Impact Strength			ISO 179
Complete Break	5.8	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179
Complete Break	36	kJ/m <sup>2</sup>	

#### Thermal

	Typical Value	Unit	Test method
Heat Deflection Temperature			
0.45 MPa, Unannealed	281	°C	ISO 75-2/B
1.8 MPa, Unannealed	237	°C	ISO 75-2/A

# Xydar® M-345

liquid crystal polymer

Injection	Typical Value	Unit
Drying Temperature	150	°C
Drying Time	6.0 to 8.0	hr
Processing (Melt) Temp	340 to 370	°C
Mold Temperature	70 to 160	°C
Clamp Tonnage	2.8 to 5.5	kN/cm <sup>2</sup>
Screw L/D Ratio	20.0:1.0 to 24.0:1.0	
Screw Compression Ratio	2.5:1.0 to 3.0:1.0	

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> 0.05% to 0.25%



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.