

TECHNYL® C 50H2 Black 46 N is an unreinforced polyamide 6 based on a non-phosphorous and non-halogenated flame retardant system, heat stabilized, for injection moulding. This product, UL94 VO @ 0,4mm, offers excellent moldability together with good stiffness.

GENERAL

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific	• Europe
Additive	• Flame Retardant	• Heat Stabilizer
Key Benefits	• Glow Wire Resistance • Good Mold Release	• UL 94 VO at 0.4 mm
Applications	• Connectivity • Electrical Parts	• Electrical/Electronic Applications
Certification/Compliance	• EC 1907/2006 (REACH) • EN 45545	• UL QMFZ2
RoHS Compliance	• RoHS Compliant	
Colors Available	• Black • Grey	• Natural Color
Forms	• Pellets	
Processing Method	• Injection Molding	
Resin ID (ISO 1043)	• PA6 FR(30)	

PROPERTIES

Typical values of properties are for Natural grades

Physical	Dry	Conditioned	Unit	Test Method
Molding Shrinkage				ISO 294-4
Across Flow	0.80		%	
Flow	0.80		%	
Water Absorption (24 hr, 23°C)	1.1		%	ISO 62
Density	1.16		g/cm³	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3500	2000	MPa	ISO 527-2/1A
Tensile Strength				
Yield, 23°C	80		MPa	ASTM D638
Yield, 23°C	75	50	MPa	ISO 527-2/1A
Break, 23°C	80		MPa	ASTM D638
Break, 23°C	60	40	MPa	ISO 527-2/1A

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strain				
Yield, 23°C	3.5	5.0	%	ISO 527-2
Break, 23°C	15		%	ASTM D638
Break, 23°C	25	38	%	ISO 527-2
Flexural Modulus				
23°C	3500		MPa	ASTM D790
23°C	3150	2000	MPa	ISO 178
Flexural Strength				
23°C	115		MPa	ASTM D790
23°C	200	70.0	MPa	ISO 178
Charpy Notched Impact Strength (23°C)	6.0	15	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	180		kJ/m²	ISO 179/1eU
Notched Izod Impact				
23°C	65		J/m	ASTM D256
23°C	3.5	15	kJ/m²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
1.8 MPa, Unannealed	75		°C	ISO 75-2/Af
Melting Temperature	222		°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Electric Strength (2.00 mm)	34	30	kV/mm	IEC 60243-1
Relative Permittivity	3.50	3.90		IEC 60250
Dissipation Factor	0.020	0.060		IEC 60250
Comparative Tracking Index				IEC 60112
Solution A	600	600	V	
Solution B	475		V	
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.40 mm	V-0			
0.8 mm	V-0			
1.6 mm	V-0			
3.2 mm	V-0			
Glow Wire Flammability Index				IEC
0.8 mm	960		°C	60695-2-12
1.6 mm	960		°C	
3.2 mm	960		°C	

Flammability	Dry	Conditioned	Unit	Test Method
Glow Wire Ignition Temperature				IEC
0.8 mm	700		°C	60695-2-13
1.6 mm	700		°C	
3.2 mm	700		°C	
Oxygen Index	36		%	ISO 4589-2

Additional Information	Dry	Unit	Test Method
European Railways Certifications			EN 45545-2
R22		HL3	
R23		HL3	
R25		HL3	

PROCESSING

Injection	Dry	Unit
Drying Temperature	80	°C
Suggested Max Moisture	0.20	%
Rear Temperature	230 to 235	°C
Middle Temperature	235 to 240	°C
Front Temperature	235 to 245	°C
Mold Temperature	60 to 90	°C

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:

- All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Solvay recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Solvay advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% Chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.

DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.



SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with ROHS Directive 2011/65/EU and 2015/863 as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

CUSTOMER SERVICES

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range on our internet product finder at the following address: <http://www.technyl.com>

Notes

Typical properties: these are not to be construed as specifications.