

# TECHNYL®

## TECHNYL® C 52G1 V30 GREY 2408CF

TECHNICAL DATA SHEET

Revised: October, 2019

TECHNYL® C 52G1 V30 Grey 2408 CF is a polyamide 6 based on a non-phosphorous and Non-halogenated flame retardant system, reinforced with 30% of glass fiber, heat stabilized, for injection moulding. This flame retardant grade with excellent moulding and electrical performance.

### GENERAL

|                          |   |
|--------------------------|---|
| Material Status          | • Commercial: Active  |
| Availability             | • Africa & Middle East • Europe   |
| Filler / Reinforcement   | • Glass Fiber, 30% Filler by Weight   |
| Additive                 | • Flame Retardant • Heat Stabilizer   |
| Key Benefits             | • Arc Resistance • UV Laser Markable<br>• Glow Wire Resistance • UL 94 V2 at 0.8 mm       |
| Applications             | • Circuit Breaker • Electrical/Electronic Applications<br>• Electrical protection devices |
| Certification/Compliance | • EC 1907/2006 (REACH) • UL QMFZ2   |
| Colors Available         | • Grey  |
| Forms                    | • Pellets   |
| Processing Method        | • Injection Molding   |
| Resin ID (ISO 1043)      | • PA6-GF30 FR(30)   |

### PROPERTIES

Typical values of properties are for Grey grades

| Physical                                | Dry Unit               | Test Method  |
|---|------------------------|--------------|
| Water Absorption (24 hr, 23°C)          | 1.0 %                  | ISO 62       |
| Density                                 | 1.38 g/cm <sup>3</sup> | ISO 1183/A   |
| Mechanical                              | Dry Unit               | Test Method  |
| Tensile Modulus (23°C)                  | 7400 MPa               | ISO 527-2/1A |
| Tensile Stress (Break, 23°C)            | 90 MPa                 | ISO 527-2/1A |
| Tensile Strain (Break, 23°C)            | 2.0 %                  | ISO 527-2    |
| Charpy Unnotched Impact Strength (23°C) | 35 kJ/m <sup>2</sup>   | ISO 179/1eU  |
| Thermal                                 | Dry Unit               | Test Method  |
| Heat Deflection Temperature             |                        |              |
| 0.45 MPa, Unannealed                    | 215 °C                 | ISO 75-2/Bf  |
| 1.8 MPa, Unannealed                     | 190 °C                 | ISO 75-2/Af  |
| Melting Temperature                     | 220 °C                 | ISO 11357-3  |



| Electrical                              | Dry Unit | Test Method |
|---|----------|-------------|
| Comparative Tracking Index (Solution A) | 500 V    | IEC 60112   |

  

| Flammability                 | Dry Unit | Test Method    |
|------------------------------|----------|----------------|
| Flame Rating                 |          | UL 94          |
| 0.8 mm                       | V-2      |                |
| 1.6 mm                       | V-2      |                |
| 3.2 mm                       | V-2      |                |
| Glow Wire Flammability Index |          | IEC 60695-2-12 |
| 1.6 mm                       | 960 °C   |                |
| 3.2 mm                       | 960 °C   |                |

## PROCESSING

| Injection              | Dry Unit      |
|------------------------|---------------|
| Drying Temperature     | 80 °C         |
| Suggested Max Moisture | 0.20 %        |
| Rear Temperature       | 230 to 235 °C |
| Middle Temperature     | 235 to 240 °C |
| Front Temperature      | 240 to 250 °C |
| Mold Temperature       | 60 to 90 °C   |

### Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

### Injection Advice:

- All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Solvay recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Solvay advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% Chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.

### DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.



## SAFETY INFORMATION

---

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

## REGULATIONS COMPLIANCE

---

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

## CUSTOMER SERVICES

---

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range on our internet product finder at the following address: <http://www.technyl.com>

### Notes

Typical properties: these are not to be construed as specifications.

