

# TECHNYL®

## TECHNYL® C 206F NATURAL

TECHNICAL DATA SHEET

Revised: June, 2017

TECHNYL® C 206F Natural is an unreinforced polyamide PA6, standard for fast injection cycles, for injection moulding. This grade has high fluidity and a good mould release.

### GENERAL

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe
Key Benefits	• Fast Molding Cycle • Good Flow • Good Mold Release
Applications	• Cable ties • Clips & Fasteners • Fittings • Valves
Certification/Compliance	• EC 1907/2006 (REACH) • UL QMFZ2
RoHS Compliance	• RoHS Compliant
Colors Available	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6

### PROPERTIES

Typical values of properties are for Natural grades

Physical	Dry	Conditioned	Unit	Test Method
Water Absorption				ISO 62
23°C, 24 hr	1.6		%	
Equilibrium, 23°C, 50% RH	3.3		%	
Density	1.14		g/cm <sup>3</sup>	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3000	1100	MPa	ISO 527-2/1A
Tensile Stress				ISO 527-2/1A
Yield, 23°C	85	45	MPa	
Break, 23°C	50	60	MPa	
Tensile Strain				ISO 527-2
Yield, 23°C	4.0	30	%	
Break, 23°C	15	> 200	%	
Flexural Modulus (23°C)	2800	1000	MPa	ISO 178
Flexural Stress (23°C)	100	40.0	MPa	ISO 178
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	4.0		kJ/m <sup>2</sup>	
23°C	5.0		88 kJ/m <sup>2</sup>	



<b>Mechanical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break			
23°C	No Break	No Break		
Notched Izod Impact Strength (23°C)	5.0	80	kJ/m <sup>2</sup>	ISO 180
<b>Thermal</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Heat Deflection Temperature				ISO 75-2/ Af
1.8 MPa, Unannealed	60		°C	
Melting Temperature	222		°C	ISO 11357-3
<b>Electrical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity	1.0E+14	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	IEC 60093
Electric Strength (2.00 mm)		18	kV/mm	IEC 60243-1
Relative Permittivity	3.40	3.90		IEC 60250
Dissipation Factor	0.023	0.10		IEC 60250
Comparative Tracking Index (Solution A)	600	V		IEC 60112
<b>Flammability</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating (3.2 mm)	V-2			UL 94
Glow Wire Ignition Temperature (0.8 mm)	675		°C	IEC 60695-2-13



## PROCESSING

Injection	Dry Unit
Drying Temperature	80 °C
Suggested Max Moisture	0.20 %
Rear Temperature	230 to 235 °C
Middle Temperature	235 to 240 °C
Front Temperature	235 to 245 °C
Mold Temperature	60 to 80 °C

### Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

#### Injection Advice:

- For unfilled polyamides, Solvay recommends the use of high alloy steel with a low chromium content. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design

## DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.



## SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

## REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with ROHS Directive 2011/65/EU and 2015/863 as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

## CUSTOMER SERVICES

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range on our internet product finder at the following address:  
<http://www.technyl.com>

### Notes

Typical properties: these are not to be construed as specifications.

