

## TECHNYL® C 216 MT30

Product Datasheet - June 2007

### Description

Polyamide PA6, 30 % mineral filled, for injection moulding.

### Product Applications

The isotropic shrinkage and the good dimensional stability make it adequate for every kind of application in which the planarity of the part is important.

This product is available in colours on request.

### Processing

The material is supplied in airtight bags, ready for use. In the case that the virgin material has absorbed moisture, it must be dried to a final moisture content less than 0.2% with a dehumidified air drying equipment at approx. 80°C.

Recommended moulding conditions :

- Barrel temperatures :
- feed zone : 225 - 230°C
- compression zone : 230 - 240°C
- front zone : 240 - 250°C
- Mould temperature : 80 - 120 °C

For more detailed information, please refer to the technical sheet "Injection moulding"

### Safety

Please refer to the Safety Data Sheet VAAF03118FS

# TECHNYL® C 216 MT30

The values of properties are for natural grade.

Properties	Standards	Unit	Values	
			d.a.m*.	Cond.**
<b>Physical</b>				
Water absorption (24 h at 23°C)	ISO 62	%	1	-
Density	ISO 1183-A	g/cm3	1.36	-
<b>Mechanical</b>				
Tensile modulus	ISO 527 type 1 A	MPa	5500	2500
Elongation at break	ISO 527 type 1 A	%	6	15
Tensile strength at break	ISO 527 type 1 A	MPa	85	50
Flexural modulus	ISO 178	MPa	5300	2000
Charpy notched impact strength	ISO 179/1eA	kJ/m2	9	20
Charpy unnotched impact strength	ISO 179/1eU	kJ/m2	65	80
Izod notched impact strength	ISO 180/1A	kJ/m2	5	15
<b>Flamability</b>				
Glow wire flammability index (thickness = 1,6)	IEC 60695-2-12	°C	850	-
<b>Thermal</b>				
Melting Temperature	ISO 11357	°C	222	-
Heat deflection temperature, 1,8 Mpa	ISO 75/Af	°C	140	-
Coef. of Linear thermal expansion normal or perpendicular ( 23°C to 85°C)	ISO 11359	E-5 / °C	4	-
<b>Electrical</b>				
Dissipation factor	IEC 60250		0.02	0.09
Volume resistivity	IEC 60093	Ohm.cm	10E14	10E10
Surface resistivity	IEC 60093	Ohm	10E12	10E10
Dielectric strength	IEC 60243	kV/mm	25	15

## Identification Code : >PA6-MD30<

The information contained in this document is supplied in good faith. It is based on the extent of our knowledge of the products as listed, and on the tests and experiments carried out in our laboratories. It is to be used only as an indication and shall not be construed in any way as a format commitment or warranty of our part. Compliance of our products with your conditions or use can only be determined pursuant to your own prior appropriate list. The listed values of properties are for natural grade, if not otherwise specified.

d.a.m\*.

Cond.\*\*



Engineering Plastics

CHALLENGING BOUNDARIES

