

Description

Unreinforced polyamide PA6 with high impact strength, for injection moulding.

Product Applications

This grade has improved impact strength and higher flexibility.

It is suitable specially to make technical parts having small or medium size, such as :

- wall plugs, electrical plugs, gaskets etc.

This product is available in natural and black.

Processing

The material is supplied in airtight bags, ready for use. In the case that the virgin material has absorbed moisture, it must be dried to a final moisture content less than 0.2% with a dehumidified air drying equipment at approx. 80°C.

Recommended moulding conditions :

- Barrel temperatures :

feed zone	220 - 230 °C
compression zone	225 - 230 °C
front zone	225 - 230 °C

- Mould temperatures : 40 - 60 °C

For more detailed information, please refer to the technical sheet "Injection moulding".

Safety

Please refer to the Safety Data Sheet LKRE5G0K8FS

TECHNYL® C 250

The values of properties are for natural grade.

Properties	Standards	Unit	Values	
			d.a.m*.	Cond.**
Physical				
Water absorption (24 h at 23°C)	ISO 62	%	1.20	-
Density	ISO 1183-A	g/cm3	1.06	-
Mechanical				
Tensile modulus	ISO 527 type 1 A	MPa	1600	500
Tensile strength at yield	ISO 527 type 1 A	MPa	38	34
Flexural modulus	ISO 178	MPa	1550	400
Flexural maximum stress	ISO 178	MPa	70	25
Charpy notched impact strength	ISO 179/1eA	kJ/m2	82	NB
Charpy unnotched impact strength	ISO 179/1eU	kJ/m2	NB	NB
Izod notched impact strength	ISO 180/1A	kJ/m2	12	85
Izod notched impact strength	ISO 180/1A	kJ/m2	80	NB
Flamability				
Flammability UL 94 (Thickness 1,6 mm)	ISO 1210/UL 94		HB	-
Thermal				
Melting Temperature	ISO 11357	°C	222	-
Heat deflection temperature, 1,8 Mpa	ISO 75/Af	°C	60	-
Coef. of Linear thermal expansion normal or perpendicular (23°C to 85°C)	ISO 11359	E-5 / °C	7	-
Coef. of Linear thermal expansion parallel (23°C to 85°C)	ISO 11359	E-5 / °C	7	-
Electrical				
Relative permittivity	IEC 60250		3.5	4
Dissipation factor	IEC 60250		0.02	0.12
Volume resistivity	IEC 60093	Ohm.cm	10E14	10E10
Surface resistivity	IEC 60093	Ohm	10E12	10E10
Dielectric strength	IEC 60243	kV/mm	-	18
Comparative tracking index sol. A	IEC 60112	Volt	600	-
Specific				
IMDS id number	Rhodia		33431649/ 1	-

Identification Code : >PA6<

The information contained in this document is supplied in good faith. It is based on the extent of our knowledge of the products as listed, and on the tests and experiments carried out in our laboratories. It is to be used only as an indication and shall not be construed in any way as a format commitment or warranty of our part. Compliance of our products with your conditions or use can only be determined pursuant to your own prior appropriate list. The listed values of properties are for natural grade, if not otherwise specified.

d.a.m*.

Cond.**



CHALLENGING BOUNDARIES

Engineering Plastics