

TECHNYL® C 226

Description	Unreinforced polyamide PA6 , with a high dyeing, for injection moulding.
--------------------	--

Applications	This grade is recommended for fast cycling offering a higher white degree and a good dyeing.
---------------------	--

This product is available in white colour.

Processing	The material is supplied in airtight bags, ready for use. In the case that the virgin material has absorbed moisture, it must be dried to a final moisture content less than 0.2% with a dehumidified air drying equipment at approx. 80°C.
-------------------	---

Recommended moulding conditions :

- Barrel temperatures :

feed zone	210 - 220°C
compression zone	220 - 230°C
front zone	225 - 235°C

- Mould temperatures : 20 - 40 °C

For more detailed information, please refer to the technical sheet "Injection moulding".

Safety	Please refer to the Material Safety Data Sheet C1
---------------	---

TECHNYL® C 226

Main properties

Values measured at 23 °C

The values of properties are for natural grade.

Properties	Standards	Unit	Values		
			EH 0 – 23 °C	EH 50 – 23 °C	
Physical	Water absorption, 24h in water at 23°C	ISO 62	%	1.2	-
	Density	ISO 1183-A	g/cm3	1.14	-
Mechanical	Tensile Modulus	ISO 527	MPa	3000	1100
	Yield stress	ISO 527	MPa	85	45
	Tensile strain at break	ISO 527	%	80	250
	Flexural modulus	ISO 178	MPa	2900	1000
	Flexural strength	ISO 178	MPa	115	40
	Charpy notched impact strength	ISO 179/1EA-1993	kJ/m2	5.2	75
	Charpy impact strength	ISO 179/1EU-1993	kJ/m2	NB	NB
	Izod notched impact strength	ISO 180	kJ/m2	4	70
Thermal	Melt temperature	ISO 3146 - C	°C	222	-
	Temper. of dimensional stability 1,8 MPa	ISO 75-2	°C	81	-
	Coef. linear expansion longit. 23°C-85°C	ASTM E 831	E-5 / °C	7	-
	Flammability UL94 thickness 1,6 mm	ISO 1210/UL 94	-	V2	-
Electrical	Relative permittivity 1MHz	IEC 250	-	3.4	3.9
	Dissipation factor 1 MHz	IEC 250	-	0.023	0.1
	Volume resistivity	IEC 93	E14.Ohm.cm	10	0.001
	Surface resistivity	IEC 93	E14.Ohm	0.1	0.001
	Dielectric strength	IEC 243-1	kV/mm	-	18
	Comparative tracking index KC	IEC 112	Volt	600	-

Identification code

>PA6<

The information contained in this document is supplied in good faith. It is based on the extent of our knowledge of the products as listed, and on the tests and experiments carried out in our laboratories. It is to be used only as an indication and shall not be construed in any way as a formal commitment or warranty on our part. Compliance of our products with your conditions of application or use can only be determined pursuant to your own prior appropriate test. The listed values of properties are for natural grade, if not otherwise specified.



Engineering Plastics

Avenue Ramboz BP 64 F-69192 Saint-Fons Cedex. Telephone: +33 (0)4 72 89 27 00 Fax: +33(0)4 72 89 27 01

RHODIA ENGINEERING PLASTICS. Société Anonyme au capital de 271 256 400 F - 393 335 104 RCS Lyon