

TECHNYL STAR®

TECHNYL STAR® SX 218 V50 BLACK Z

TECHNICAL DATA SHEET

Revised: February, 2018

TECHNYL STAR® SX 218 V50 Black Z is based on a patented high flow polyamide 6 resin (Technylstar), heat stabilized, reinforced with 50% of glass fibre, for injection moulding. Due to its outstanding flow characteristics, this grade allows more freedom in mould and part design versus a standard polyamide solutions.

GENERAL

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific	• Europe • North America
Filler / Reinforcement	• Glass Fiber, 50% Filler by Weight	
Additive	• Heat Stabilizer	
Key Benefits	• Good Dimensional Stability • High Flow • Heat Stabilized (Inorganic)	• High Stiffness • Superior Surface Finish
Applications	• Automotive applications • Bicycles component • Electrical/Electronic Applications • External rear mirror bracket • Fixation for Photovoltaic	• Motor pulleys • Power tool housings • Sports equipment • Suspension components • Switch, Plug, Control & Sockets
Certification/Compliance	• EC 1907/2006 (REACH)	• UL QMFZ2
RoHS Compliance	• RoHS Compliant	
Automotive Specifications	• GM GMP.PA6.065	
Colors Available	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	• MuCell® Injection Molding
Resin ID (ISO 1043)	• PA6-GF50	

PROPERTIES

Typical values of properties are for Black grades

Physical	Dry	Conditioned	Unit	Test Method
Molding Shrinkage				ISO 294-4
Across Flow	0.60		%	
Flow	0.20		%	
Water Absorption				ISO 62
24 hr, 23°C	0.72		%	
Equilibrium, 23°C, 50% RH	1.1		%	
Density	1.56		g/cm ³	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	17500	11000	MPa	ISO 527-2/1A



Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress				ISO 527-2/1A
Yield, 23°C	230	155	MPa	
Break, 23°C	230	155	MPa	
Tensile Elongation				
Break, 23°C	2.6		%	ASTM D638
Break, 23°C	2.5	3.7	%	ISO 527-2
Flexural Modulus				
23°C	14000		MPa	ASTM D790
23°C	15000	10300	MPa	ISO 178
Flexural Strength				
23°C	320		MPa	ASTM D790
23°C	350	250	MPa	ISO 178
Charpy Notched Impact Strength (23°C)	15	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				
23°C	85	95	kJ/m ²	ISO 179/1eU
23°C	80	90	kJ/m ²	ISO 179/1fU
Notched Izod Impact				
23°C	180		J/m	ASTM D256
23°C	15	22	kJ/m ²	ISO 180
Unnotched Izod Impact Strength (23°C)	90	95	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
1.8 MPa, Unannealed	210		°C	ISO 75-2/ Af
Melting Temperature	220		°C	ISO 11357-3
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (3.2 mm)	HB			UL 94

PROCESSING

	Dry	Unit
Injection		
Drying Temperature	80	°C
Suggested Max Moisture	0.20	%
Rear Temperature	230 to 235	°C
Middle Temperature	235 to 245	°C
Front Temperature	245 to 250	°C
Mold Temperature	60 to 90	°C

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:

- For reinforced polyamides, Solvay recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
 - The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design
-

DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.



SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with ROHS Directive 2011/65/EU and 2015/863 as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

CUSTOMER SERVICES

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:


- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range on our internet product finder at the following address: <http://www.technyl.com>



MULTIPOINT DATA

Isothermal Stress vs. Strain (ISO 11403-1)



Notes

Typical properties: these are not to be construed as specifications.

