



## TECHNYL A 60G2 V30 NATURAL

### Description

TECHNYL® A 60G2 V30 is a 30% GF reinforced organophosphorous flame retarded grade based on a patented high flow polyamide 66 resin. This product is heat stabilized and provides optimized injection molding performance.

This product is available in natural colors. Laser Marking grade optimized available upon request.

### Key Properties

Outstanding flame retardancy  
UL 5VA at 1.6mm  
Excellent electrical performance  
Excellent all-round mechanical properties

### Benefits

This product offers excellent flame retardancy properties (UL 94, 5VA, GWIT) combined with excellent processing, mechanical and electrical performance.

It can withstand temperatures of 160°C for over 6000 hours and has a UL F1 rating for weatherability resistance.

### Applications

It is ideally suited for industrial controls, power distribution or appliance applications such as MCBs and contactors. The long term thermal performance of this grade also makes it ideal for under-the-bonnet Auto applications.

**Properties**

Typical values of properties are for natural grades

	Standards	Unit	Values	
			d.a.m.	Cond.
<b>Physical</b>				
Density	ISO 1183/A	g/cm <sup>3</sup>	1,46	
<b>Mechanical</b>				
Tensile Modulus	ISO 527 Type 1A	MPa	11500	
Tensile strength at break	ISO 527 Type 1A	MPa	150	
Elongation at break	ISO 527 Type 1A	%	2,50	
Charpy unnotched impact strength (23 °C)	ISO 179/1eU	kJ/m <sup>2</sup>	55	
<b>Flammability</b>				
Flammability (Thickness: 0,8 mm)	ISO 1210 / UL94		V0	
Flammability (Thickness: 1,6 mm)	ISO 1210 / UL94		V0	
Flammability (Thickness: 3,2 mm)	ISO 1210 / UL94		V0	
Glow Wire Flammability Index (Thickness: 0,8 mm)	ISO 60695-2-12	°C	960	
Glow Wire Flammability Index (Thickness: 1,6 mm)	ISO 60695-2-12	°C	960	
Glow Wire Flammability Index (Thickness: 3,2 mm)	ISO 60695-2-12	°C	960	
Glow Wire Ignition Temperature (Thickness: 0,8 mm)	ISO 60695-2-13	°C	800	
Glow Wire Ignition Temperature (Thickness: 1,6 mm)	ISO 60695-2-13	°C	850	
<b>Thermal</b>				
Melting Temperature	ISO 11357	°C	262	
Heat deflection temperature (1,8 MPa)	ISO 75/Af	°C	247	
Heat deflection temperature (0,45 MPa)	ISO 75/Bf	°C	256	
<b>Electrical</b>				
Comparative tracking index (Sol A)	IEC 60112	V	600	
<b>Specific</b>				
Identification code			PA66-GF30 FR(40)	

d.a.m. = dry as moulded

Cond = conditioned

**Disclaimer**

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANDABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.

## Processing Guide

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment.

Recommended Maximum water content: 0,2 %

Drying conditions: 80 °C

### Recommended moulding conditions

Barrel Temperatures:

- feed zone 265 - 275 °C

- compression zone 265 - 275 °C

- mixing zone 270 - 280 °C

Mould temperatures: 60 - 90 °C

### Steel advice for tools

All reinforced flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues can be worsened by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Solvay recommends to use the advised processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retarded compounds, Solvay advises to use a steel containing high chromium & high carbon content (minimum concentration of 16% Chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds processing, please refer to your equipment manufacturers.

## Safety information

Detailed information regarding safety are available on the safety data sheet (SDS).  
SDS is sent with the first material order, or available by contacting our customer services

## Regulations compliance

Grades produced or imported in Europe comply with directive 453/2010/EC, which amends REACH directive 1907/2006/EC

This grade complies with RoHS directive 2002/95/EC

Unless specified, this grade is not suitable for food contact, medical devices or toy applications

## Customer services

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range by on Technyl.com and the link to the product finder and brochures at the following address:

<http://www.technyl.com/en/download/brochures/index.html>

## Yellow card

**Component - Plastics** [\[guide info\]](#)
**E44716**
**SOLVAY ENGINEERING PLASTICS GBU**

QUARTIER BELLE-ETOILE, AVE RAMBOZ, BOITE POSTALE 64, ST FONS CEDEX 69192 FR

**A 60G2 V30(f1)**

Polyamide 66 (PA66), glass reinforced, "Technyl", furnished as pellets

	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
Color	0.8	V-0	0	0	130	105	120
ALL	1.5	V-0, 5VA	0	0	130	115	130
	3.0	V-0, 5VA	0	0	130	115	130

Comparative Tracking Index (CTI): 0

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): -

 Volume Resistivity (10<sup>x</sup> ohm-cm): -

 High-Voltage Arc Tracking Rate  
(HVTR): -

 High Volt, Low Current Arc Resis  
(D495): 5

Dimensional Stability (%): -

(f1) - Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C.

NOTE - Materials designated "Technyl" may be prefixed by the letters "TY".

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

 Report Date: 2004-11-29  
 Last Revised: 2013-07-10

© 2015 UL LLC


**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	0.8	V-0 (ALL)
			1.5	V-0, 5VA (ALL)
			3.0	V-0, 5VA (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	0.8	960
			1.5	960
			3.0	960
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	0.8	800
			1.5	825
			3.0	825
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m <sup>2</sup>	-	-
ISO Izod Impact	ISO 180	kJ/m <sup>2</sup>	-	-
ISO Charpy Impact	ISO 179-2	kJ/m <sup>2</sup>	4.0	196