

TECHNYL® A 205F NATURAL P

Product Datasheet - June 2007

Description

Unreinforced polyamide 66, high fluidity, fast cycling grade, with improved white index, for injection moulding

Product Applications

TECHNYL® A 205F NATURAL P offers two main advantages: excellent filling qualities and UL 94 V2 under 0.4 mm. It is particularly suitable for the moulding of long parts with thin wall sections, such as:

- cable ties and fasteners,
- connectors.

This product is available in natural, black and in colours on request.

Processing

The material is supplied in airtight bags, ready for use. In the case that the virgin material has absorbed moisture, it must be dried to a final moisture content of less than 0,2% with a dehumidified air drying equipment at approx 80°C.

Recommended moulding conditions:

Barrel temperatures :

- feed zone 270 - 275°C
- compression zone 280 - 285°C
- front zone 285 - 290°C

Mould temperatures: 60 at 80°C

For more detailed information , please refer to the technical sheet Injection moulding.

Safety

Please refer to the Safety Data Sheet TGJ1H7HT8FS



TECHNYL® A 205F NATURAL P

The values of properties are for natural grade.

Properties	Standards	Unit	Values	
			d.a.m*.	Cond.**
Physical				
Water absorption (24 h at 23°C)	ISO 62	%	1.20	-
Density	ISO 1183-A	g/cm3	1.14	-
Molding shrinkage Parallel (1) (RHODIA-EP)	RHODIA-EP	%	1.90	-
Molding shrinkage normal or perpendicular (1) (Rhodia EP)	RHODIA-EP	%	1.90	-
Molding Shrinkage Isotropy	RHODIA-EP		1	-
Mechanical				
Tensile modulus	ISO 527 type 1 A	MPa	3200	1600
Tensile strength at yield	ISO 527 type 1 A	MPa	85	50
Elongation at yield	ISO 527 type 1 A	%	4	10
Tensile strength at break	ISO 527 type 1 A	MPa	60	40
Flexural modulus	ISO 178	MPa	2900	1300
Flexural maximum stress	ISO 178	MPa	120	50
Charpy notched impact strength	ISO 179/1eA	kJ/m2	4.5	8
Charpy unnotched impact strength	ISO 179/1eU	kJ/m2	NB	NB
Izod notched impact strength	ISO 180/1A	kJ/m2	4.5	6
Flamability				
Glow wire flammability index (thickness = 1,6)	IEC 60695-2-12	°C	850	-
Limit Oxygen index	ISO 4589		28.5	-
Thermal				
Melting Temperature	ISO 11357	°C	263	-
Electrical				
Relative permittivity	IEC 60250		2.90	3
Dissipation factor	IEC 60250		0.03	0.08
Volume resistivity	IEC 60093	Ohm.cm	10E14	10E12
Surface resistivity	IEC 60093	Ohm	50E13	10E12
Dielectric strength	IEC 60243	kV/mm	27	26
Comparative tracking index sol. A	IEC 60112	Volt	600	600
Comparative tracking index sol. B	IEC 60112	Volt	550	-
Specific				
IMDS id number	Rhodia		4745432 / 3	-

Identification Code : >PA66<

The information contained in this document is supplied in good faith. It is based on the extent of our knowledge of the products as listed, and on the tests and experiments carried out in our laboratories. It is to be used only as an indication and shall not be construed in any way as a format commitment or warranty of our part. Compliance of our products with your conditions or use can only be determined pursuant to your own prior appropriate list. The listed values of properties are for natural grade, if not otherwise specified.

d.a.m*.

Cond.**



Engineering Plastics

