TECHNYL® A 206 NATURAL Z

Product Datasheet - June 2007

Description

Unreinforced polyamide PA66 , medium viscosity , for injection moulding.

Product Applications

TECHNYL A 206 NATURAL Z offers two main advantages: its good resilience and its excellent filling quality of moulds .This grade is particularly suitable for the moulding of parts with thin wall sections , such as: small wheels and gears , and small components for telephones and electrical appliances .

This product is only available in natural .

Processing

The material is supplied in airtight bags, ready for use. In the case that the virgin material has absorbed moisture, it must be dried to a final moisture content of less than 0,2% with a dehumidified air drying equipment at approx 80°C.
Recommended moulding conditions: Barrel temperatures:
- feed zone 250 - 270°C
- compression zone 260 - 270°C
- front zone 270 - 280°C

Mould temperatures: 60 at 80°C
For more detailed information, please refer to the technical sheet Injection moulding..

Safety

Please refer to the Safety Data Sheet HUKNH86R8FS

Postal Adress Rhodia Polyamide Engineering Plastics : Avenue Ramboz BP 64 69192 Saint-Fons Cedex France Phone : +33.4.72.89.27.00 Fax : +33.4.72.89.27.01.
Company Name : Rhodia Operations Registered Office : 40, rue de la Haie-Coq 93306 Aubervilliers Cedex France - Phone : + 33 1 53 56 50 00 Fax : +33 1 53 56 55 55.

TECHNYL® A 206 NATURAL Z

The values of properties are for natural grade.

Properties	Standards	Unit	Values	
			d.a.m*.	Cond.**
Physical				
Water absorption (24 h at 23°C)	ISO 62	%	1.20	-
Density	ISO 1183-A	g/cm3	1.14	-
Molding shrinkage Parallel (1) (RHODIA-EP)	RHODIA-EP	%	1.90	-
Molding shrinkage normal or perpendicular (1) (Rhodia EP)	RHODIA-EP	%	1.90	-
Molding Shrinkage Isotropy	RHODIA-EP		1	-
Mechanical				
Tensile modulus	ISO 527 type 1 A	MPa	3100	1700
Tensile strength at yield	ISO 527 type 1 A	MPa	86	60
Elongation at yield	ISO 527 type 1 A	%	5	18
Tensile strength at break	ISO 527 type 1 A	MPa	56	50
Flexural modulus	ISO 178	MPa	2900	1400
Flexural maximum stress	ISO 178	MPa	120	60
Charpy notched impact strength	ISO 179/1eA	kJ/m2	4.5	14
Charpy unnotched impact strength	ISO 179/1eU	kJ/m2	NB	NB
Izod notched impact strength	ISO 180/1A	kJ/m2	5	15
Flamability				
Flammability UL 94 (Thickness 1,6 mm)	ISO 1210/UL 94		V2	-
Thermal				
Melting Temperature	ISO 11357	°C	263	-
Heat deflection temperature, 1,8 Mpa	ISO 75/Af	°C	90	-
Coef. of Linear thermal expansion parallel (23°C to 85°C)	ISO 11359	E-5 / °C	7	-
Electrical				
Relative permittivity	IEC 60250		3.30	4
Dissipation factor	IEC 60250		0.02	0.11
Volume resistivity	IEC 60093	Ohm.cm	10E14	90E10
Surface resistivity	IEC 60093	Ohm	20E12	20E11
Dielectric strength	IEC 60243	kV/mm	27	-
Comparative tracking index sol. A	IEC 60112	Volt	600	600
Specific				
IMDS id number	Rhodia		4606522 / 3	-

Identification Code : >PA66<

The information contained in this document is supplied in good faith. It is based on the extent of our knowledge of the products as listed, and on the tests and experiments carried out in our laboratories. It is to be used only as an indication and shall not be construed in any way as a format commitment or warranty of our part. Compliance of our products with your conditions or use can only be determined pursuant to your own prior appropriate list. The listed values of properties are for natural grade, if not otherwise specified.

d.a.m*.

Cond.**

Postal Adress Rhodia Polyamide Engineering Plastics : Avenue Ramboz BP 64 69192 Saint-Fons Cedex France Phone : +33.4.72.89.27.00 Fax : +33.4.72.89.27.01.
Company Name : Rhodia Operations Registered Office : 40, rue de la Haie-Coq 93306 Aubervilliers Cedex France - Phone : + 33 1 53 56 50 00 Fax : +33 1 53 56 55 55.