



SOLVAY ENGINEERING PLASTICS GBU  
QUARTIER BELLE-ETOILE, AVE RAMBOZ, BOITE POSTALE 64, ST FONS CEDEX 69192 FR



Technyl: A 218 V(xx)

Polyamide 66 (PA66), pellets, glass reinforced

(xx) - Represents range of glass filling 1-34 percent.

NOTE - Materials designated "Technyl" may be prefixed by the letters "TY".

可燃性	值	测试方法
UL 阻燃等级		
0.8 mm, NC, BK	HB	UL 94
1.5 mm, NC, BK	HB	UL 94
3.0 mm, NC, BK	HB	UL 94
3.0 mm, NC, BK	HB40	IEC 60695-11-10, -20
0.8 mm, NC, BK	HB75	IEC 60695-11-10, -20
1.5 mm, NC, BK	HB75	IEC 60695-11-10, -20
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746
1.5 mm	PLC 4	
3.0 mm	PLC 3	
高电弧燃烧指数(HAI)		UL 746
1.5 mm	PLC 0	
3.0 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 1	UL 746
热性能	值	测试方法
RTI Elec		UL 746
0.8 mm	120 °C	
1.5 mm	120 °C	
3.0 mm	120 °C	
RTI Imp		UL 746
0.8 mm	75.0 °C	
1.5 mm	75.0 °C	
3.0 mm	95.0 °C	
RTI		UL 746
0.8 mm	90.0 °C	
1.5 mm	95.0 °C	
3.0 mm	95.0 °C	