

TECHNYL®

TECHNYL® AR 218 V30 BLACK

TECHNICAL DATA SHEET

Revised: April, 2017

TECHNYL® AR 218 V30 Black is a polyamide 66, reinforced with 30% of glass fiber, heat stabilized, for injection moulding. It contains recycled materials. This grade offers a good combination between thermal and mechanical properties.

GENERAL

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer
Key Benefits	• Heat Stabilized (Inorganic) • Recycled
Applications	• Fans and shrouds • General purpose • Office chairs
Certification/Compliance	• EC 1907/2006 (REACH)
RoHS Compliance	• RoHS Compliant
Automotive Specifications	• GM GMW15702-017501 PA66-GF30 Color: Black • IMDS ID 414874974 Color: Black
Colors Available	• Black
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66-GF30

PROPERTIES

Typical values of properties are for Black grades

Physical	Dry	Conditioned	Unit	Test Method
Water Absorption				ISO 62
24 hr, 23°C	0.80		%	
Saturation, 23°C	5.3		%	
Equilibrium, 23°C, 50% RH	1.7		%	
Density	1.37		g/cm ³	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9900	6300	MPa	ISO 527-2/1A
Tensile Stress (Break, 23°C)	150	90	MPa	ISO 527-2/1A
Tensile Strain (Break, 23°C)	2.4	4.0	%	ISO 527-2
Flexural Modulus (23°C)	7000	5000	MPa	ISO 178
Flexural Strength				
23°C	220		MPa	ASTM D790
23°C	200	135	MPa	ISO 178

Solvay Engineering Plastics

www.solvay.com - www.technyl.com

Tel: 00 800 55 400 600

technyl-emea@solvay.com - Europe, Middle East, Africa

technyl-apac@solvay.com - Asia Pacific

technyl-americas@solvay.com - Americas

Page: 1 of 4



SOLVAY

asking more from chemistry®

Mechanical	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0		kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	45	55	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	8.0		kJ/m ²	ISO 180
Unnotched Izod Impact Strength (23°C)	6.0	11	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	240		°C	ISO 75-2/Bf
1.8 MPa, Unannealed	235		°C	ISO 75-2/Af
Melting Temperature	260		°C	ISO 11357-3
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.6 mm)	HB			UL 94
Glow Wire Flammability Index (1.6 mm)	650		°C	IEC 60695-2-12
Oxygen Index	23		%	ISO 4589-2

PROCESSING

Injection	Dry	Unit
Drying Temperature	80	°C
Suggested Max Moisture	0.20	%
Rear Temperature	270 to 280	°C
Middle Temperature	275 to 285	°C
Front Temperature	280 to 290	°C
Mold Temperature	70 to 100	°C

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:

- For reinforced polyamides, Solvay recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
 - The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design
-

DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.



SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with ROHS Directive 2011/65/EU and 2015/863 as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

CUSTOMER SERVICES

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range on our internet product finder at the following address: <http://www.technyl.com>

Notes

Typical properties: these are not to be construed as specifications.

