



TECHNYL C 218L V30

Description

TECHNYL C 218L V30 is a polyamide 6 reinforced with 30% glass fibre and UV stabilized for injection moulding.

This product is available in black and grey colors.

Benefits

This grade offers an excellent superficial aspect and excellent dimensional stability. It has good thermal and impact resistance.

Applications

It is used in all sector of industry mainly in automotive industry as :

- external rear mirror support,
- external door handle
- interior trims & switches...

Key Properties

Excellent surface aspect
Dimensional stability
UV stabilised

Properties

Typical values of properties are for black grades

	Standards	Unit	Values	
			d.a.m.	Cond.
Physical				
Water absorption(24h at 23°C)	ISO 62	%	0,95	
Density	ISO 1183/A	g/cm3	1,35	
Molding shrinkage Parallel	RHODIA	%	0,35	
Molding shrinkage normal or perpendicular	RHODIA	%	0,65	
Mechanical				
Tensile Modulus	ISO 527 Type 1A	MPa	9700	6200
Tensile strength at break	ISO 527 Type 1A	MPa	165	120
	ASTM D-638	MPa	160	
Elongation at break	ISO 527 Type 1A	%	3,80	4,50
	ASTM D-638	%	3	
Flexural modulus	ISO 178	MPa	14300	
	ASTM D-790	MPa	8500	
Flexural maximum stress	ASTM D-790	MPa	230	
Charpy notched impact strength	ISO 179/1eA	kJ/m2	8	
Charpy unnotched impact strength	ISO 179/1eU	kJ/m2	70	
Izod notched impact strength	ASTM D256	J/m	110	
Flammability				
Flammability (Thickness: 3,2 mm)	ISO 1210 / UL94		HB	
Glow Wire Flammability Index (Thickness: 1,6 mm)	IEC 60695-2-12	°C	650	
Limit Oxygen Index	ISO 4589		23	
Thermal				
Melting Temperature	ISO 11357	°C	222	
Heat deflection temperature (0,45 MPa)	ISO 75/Af	°C	210	
Heat deflection temperature (1,8 MPa)	ISO 75/Af	°C	208	
	ASTM D-648	°C	205	
Electrical				
Comparative tracking index (Sol A)	IEC 60112	V	550	475
Dielectric strength	IEC 60243	kV/mm		22
Dissipation factor	IEC 60250		0,020	0,009
Relative permittivity	IEC 60250		3,80	4,50
Volume resistivity	IEC 60093	Ohm/cm	1E 15	1E 11
Specific				
Identification code				PA6-GF30

Standards**Unit****Values**

d.a.m.

Cond.

d.a.m. = dry as moulded
 Cond = conditioned

Processing Guide

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment.

Recommended Maximum water content: 0,2 %

Drying conditions: 80 °C

Recommended moulding conditions

Barrel Temperatures:

- feed zone 230 - 235 °C
- compression zone 235 - 240 °C
- mixing zone 240 - 250 °C

Mould temperatures: 60 - 90 °C

Steel advice for tools For reinforced polyamide (glass fibre, glass sphere, mineral fibre...), Solvay recommends the use of steel with a high content of Carbon and purified for polishing to avoid or limit the abrasion. For example: Z38CDV5W or Z160CDV12.

Disclaimer

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANDABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.

Safety information

Detailed information regarding safety are available on the safety data sheet (SDS).
SDS is sent with the first material order, or available by contacting our customer services

Regulations compliance

Grades produced or imported in Europe comply with directive 453/2010/EC, which amends REACH directive 1907/2006/EC

This grade complies with RoHS directive 2002/95/EC

Unless specified, this grade is not suitable for food contact, medical devices or toy applications

Customer services

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range by on Technyl.com and the link to the product finder and brochures at the following address:

<http://www.technyl.com/en/download/brochures/index.html>