

# TECHNYL®

## TECHNYL® B 216 V30 GREY 2472 CF

TECHNICAL DATA SHEET

Revised: April, 2017

TECHNYL® B 216 V30 Grey 2472 CF is a Copolyamide 66/6, reinforced with 30% of glass fibre, for injection moulding. This grade offers an excellent combination between impact resistance, rigidity, thermal resistance and surface appearance.

### GENERAL

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Key Benefits	• Good Flow • Good Mold Release • Good Surface Finish
Applications	• Automotive applications • Consumer and Industrial applications
Certification/Compliance	• EC 1907/2006 (REACH)
Colors Available	• Black • Grey • Natural Color
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66/6-GF30

### PROPERTIES

Typical values of properties are for Black grades

Physical	Dry	Conditioned	Unit	Test Method
Water Absorption (24 hr, 23°C)	0.95		%	ISO 62
Density	1.37		g/cm <sup>3</sup>	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9800	6500	MPa	ISO 527-2/1A
Tensile Stress (Break, 23°C)	185	115	MPa	ISO 527-2/1A
Tensile Strain (Break, 23°C)	3.0	7.0	%	ISO 527-2
Flexural Modulus (23°C)	8300	4700	MPa	ISO 178
Flexural Stress (23°C)	235	140	MPa	ISO 178
Charpy Notched Impact Strength (23°C)	11	16	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	80	92	kJ/m <sup>2</sup>	ISO 179/1eU
Notched Izod Impact Strength (23°C)	11	19	kJ/m <sup>2</sup>	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/Af
1.8 MPa, Unannealed	230		°C	
Melting Temperature	242		°C	ISO 11357-3



Electrical	Dry	Conditioned Unit	Test Method
Surface Resistivity	6.0E+15	1.0E+14 ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+15 ohms·cm	IEC 60093
Electric Strength (2.00 mm)	30	26 kV/mm	IEC 60243-1
Relative Permittivity	3.00	4.00	IEC 60250
Dissipation Factor	0.020	0.10	IEC 60250
Comparative Tracking Index			IEC 60112
Solution A	550	475 V	
Solution B	500	V	
Flammability	Dry	Conditioned Unit	Test Method
Flame Rating (1.6 mm)	HB		UL 94
Oxygen Index	23	%	ISO 4589-2

## PROCESSING

Injection	Dry Unit
Drying Temperature	80 °C
Suggested Max Moisture	0.20 %
Rear Temperature	255 to 265 °C
Middle Temperature	260 to 270 °C
Front Temperature	270 to 280 °C
Mold Temperature	70 to 100 °C

### Injection Notes

---

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

#### Injection Advice:

- For reinforced polyamides, Solvay recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
  - The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design
- 

### DISCLAIMER

---

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.



### SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

### REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

### CUSTOMER SERVICES

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range on our internet product finder at the following address: <http://www.technyl.com>

#### Notes

Typical properties: these are not to be construed as specifications.

