



TECHNYL B 738 MX15

Description

TECHNYL B 738 MX15 is a copolyamide 6.6, reinforced with 15% of mineral filler, for injection moulding.

This product is available in black and grey colors.

Benefits

This grade offers good mechanical Properties, good superficial aspect and dimensional stability.

Applications

It is indicated for automotive and electrical industry. Ex.: Wheel Cover

Key Properties

Good surface aspect
Mechanical performance

Properties

Typical values of properties are for grey grades

	Standards	Unit	Values	
			d.a.m.	Cond.
Physical				
Water absorption(24h at 23°C)	ISO 62	%	1,17	
Density	ISO 1183/A	g/cm3	1,22	
Mechanical				
Tensile Modulus	ISO 527 Type 1A	MPa	4300	
Tensile strength at break	ISO 527 Type 1A	MPa	59	
Elongation at break	ISO 527 Type 1A	%	3	
Flexural modulus	ISO 178	MPa	3700	
Flexural maximum stress	ISO 178	MPa	100	
Charpy unnotched impact strength	ISO 179/1eU	kJ/m2	60	
Thermal				
Melting Temperature	ISO 3146-A	°C	244	
Specific				
Identification code				PA66/6-MD15

d.a.m. = dry as moulded

Cond = conditioned

Disclaimer

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANDABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.

Processing Guide

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment.

Recommended Maximum water content: 0,2 %

Drying conditions: 80 °C

Recommended moulding conditions

Barrel Temperatures:

- feed zone	255 - 265 °C
- compression zone	260 - 270 °C
- mixing zone	270 - 280 °C
Mould temperatures:	70 - 100 °C

Steel advice for tools For reinforced polyamide (glass fibre, glass sphere, mineral fibre...), Solvay recommends the use of steel with a high content of Carbon and purified for polishing to avoid or limit the abrasion. For example: Z38CDV5W or Z160CDV12.

Safety information

Detailed information regarding safety are available on the safety data sheet (SDS).
SDS is sent with the first material order, or available by contacting our customer services

Regulations compliance

Grades produced or imported in Europe comply with directive 453/2010/EC, which amends REACH directive 1907/2006/EC

This grade complies with RoHS directive 2002/95/EC

Unless specified, this grade is not suitable for food contact, medical devices or toy applications

Customer services

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range by on Technyl.com and the link to the product finder and brochures at the following address:
<http://www.technyl.com/en/download/brochures/index.html>