

AvaSpire® AV-651 GF30

polyaryletherketone

AvaSpire® AV-651 GF30 is a 30% glass fiber reinforced polyaryletherketone (PAEK) that has been specifically formulated to provide higher mechanical strength and stiffness than unfilled AV-651 resin. This resin offers chemical resistance nearly equivalent to glass fiber-reinforced PEEK in most chemicals, with a lower heat deflection temperature.

These properties make it well suited for applications in healthcare, transportation, electronics, chemical processing and other industrial uses.

- Beige: AvaSpire® AV-651 GF30 BG 20
- Black: AvaSpire® AV-651 GF30 BK 95

General

Material Status	• Commercial: Active	
Availability	<ul style="list-style-type: none"> • Africa & Middle East • Asia Pacific • Europe 	<ul style="list-style-type: none"> • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight	
Features	<ul style="list-style-type: none"> • Autoclave Sterilizable • Biocompatible • Chemical Resistant • E-beam Sterilizable • Ethylene Oxide Sterilizable • Fatigue Resistant • Flame Retardant • Good Dimensional Stability • Good Sterilizability 	<ul style="list-style-type: none"> • Heat Sterilizable • High Heat Resistance • High Stiffness • High Strength • Radiation (Gamma) Resistant • Radiation Sterilizable • Radiotranslucent • Steam Resistant • Steam Sterilizable
Uses	<ul style="list-style-type: none"> • Aircraft Applications • Connectors • Dental Applications • Electrical/Electronic Applications • Film • Hospital Goods 	<ul style="list-style-type: none"> • Industrial Applications • Medical Devices • Medical/Healthcare Applications • Seals • Surgical Instruments
Agency Ratings	• ISO 10993	
RoHS Compliance	• Contact Manufacturer	
Appearance	• Beige	• Black
Forms	• Pellets	
Processing Method	<ul style="list-style-type: none"> • Injection Molding • Machining 	• Profile Extrusion

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.52		ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage ¹			ASTM D955
Flow : 3.18 mm	0.20 to 0.40	%	
Across Flow : 3.18 mm	1.3 to 1.5	%	
Water Absorption (24 hr)	0.20	%	ASTM D570

AvaSpire® AV-651 GF30

polyaryletherketone

Mechanical	Typical Value	Unit	Test method
Tensile Modulus			
-- ²	9900	MPa	ASTM D638
--	10400	MPa	ISO 527-2/1A/1
Tensile Stress			
Yield, 5.00 mm	162	MPa	ISO 527-2/1A/5
-- ²	156	MPa	ASTM D638
Tensile Elongation			
Break ²	2.9	%	ASTM D638
Break	2.9	%	ISO 527-2/1A/5
Flexural Modulus			
--	9400	MPa	ASTM D790
--	9700	MPa	ISO 178
Flexural Strength			
--	234	MPa	ASTM D790
--	228	MPa	ISO 178
Compressive Strength	168	MPa	ASTM D695
Shear Strength	82.6	MPa	ASTM D732
Impact	Typical Value	Unit	Test method
Notched Izod Impact			
--	110	J/m	ASTM D256
--	12	kJ/m ²	ISO 180
Unnotched Izod Impact			
--	960	J/m	ASTM D4812
--	64	kJ/m ²	ISO 180
Hardness	Typical Value	Unit	Test method
Rockwell Hardness (M-Scale)	101		ASTM D785
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Annealed	213	°C	
Glass Transition Temperature	158	°C	ASTM D3418
Peak Melting Temperature	345	°C	ASTM D3418
CLTE - Flow (-50 to 50°C)	1.7E-5	cm/cm/°C	ASTM E831
Specific Heat			DSC
50°C	1270	J/kg/°C	
200°C	1650	J/kg/°C	
Thermal Conductivity	0.30	W/m/K	ASTM E1530
Electrical	Typical Value	Unit	Test method
Surface Resistivity	> 1.9E+17	ohms	ASTM D257
Volume Resistivity	2.0E+17	ohms·cm	ASTM D257
Dielectric Strength (3.00 mm)	17	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	3.61		
1 kHz	3.63		
1 MHz	3.58		

AvaSpire® AV-651 GF30

polyaryletherketone

Electrical	Typical Value	Unit	Test method
Dissipation Factor			ASTM D150
60 Hz	2.0E-3		
1 kHz	0.0		
1 MHz	4.0E-3		
Flammability	Typical Value	Unit	Test method
Flame Rating			UL 94
0.8 mm	V-1		
1.6 mm	V-0		
Fill Analysis	Typical Value	Unit	Test method
Melt Viscosity (400°C, 1000 sec ⁻¹)	410	Pa·s	ASTM D3835
Injection	Typical Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0	hr	
Rear Temperature	365	°C	
Middle Temperature	371	°C	
Front Temperature	377	°C	
Nozzle Temperature	382	°C	
Processing (Melt) Temp	366 to 388	°C	
Mold Temperature	160 to 190	°C	
Injection Rate	Fast		
Screw Compression Ratio	2.0:1.0 to 3.0:1.0		

Notes

Typical properties: these are not to be construed as specifications.

¹ 5" x 0.5" x 0.125" bars

² 5.0 mm/min

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.

