

## AV-651

AvaSpire AV-651 is an unreinforced modified PEEK (polyetheretherketone) that offers improved ductility and impact strength relative to PEEK, with higher chemical and environmental stress cracking resistance than AvaSpire AV-650. It has been specifically formulated for applications requiring a balance of chemical resistance and mechanical strength along with good part aesthetics, bridging the performance gaps within the ultra polymers space. Plus, AvaSpire AV-651 generally offers improved part economics relative to unmodified PEEK resin.

These properties make it well-suited for applications in healthcare, transportation, electronics, chemical processing, and other industrial uses.

AvaSpire AV-651 can be easily processed by typical injection molding and extrusion methods using standard equipment.

### Typical Properties of AvaSpire AV-651 Resin

Property	ASTM Test Method	Typical Values <sup>(1)</sup>			
		U.S. Customary Units		SI Units	
		Value	Units	Value	Units
<b>Mechanical</b>					
Tensile Strength	D 638	12.6	kpsi	87	MPa
Tensile Modulus	D 638	450	kpsi	3.1	GPa
Tensile Elongation at Yield	D 638	6.2	%	6.2	%
Tensile Elongation at Break	D 638	50-100	%	50-100	%
Flexural Strength	D 790	18.9	kpsi	130	MPa
Flexural Modulus	D 790	450	kpsi	3.1	GPa
Izod Impact, Notched	D 256	1.3	ft-lb/in	70	J/m
Izod Impact, Unnotched	D 4812	no break	ft-lb/in	no break	J/m
<b>Thermal</b>					
Deflection Temperature <sup>(2)</sup> at 264 psi (1.82 MPa)	D 648	374	°F	190	°C
Glass Transition Temperature	D 3417	316	°F	158	°C
Melting Point	D 3417	644	°F	340	°C
Coefficient Linear Thermal Expansion <sup>(3)</sup>	E 831	26	µin/in°F	47	µm/m°C
<b>General and Fabrication</b>					
Specific Gravity	D 792	1.29		1.29	
Water Absorption, 24 hours	D 570	0.2	%	0.2	%
Melt Flow, 400°C, 2.16 kg	D 1238	23	g/10 min	23	g/10 min

<sup>(1)</sup> Properties are typical of limited production and final specification ranges may vary.

<sup>(2)</sup> Measured on annealed specimens

<sup>(3)</sup> Measured in the flow direction over the temperature range of -50°C to 50°C

## Drying

AvaSpire AV-651 resins must be dried completely prior to melt processing. Incomplete drying will result in defects in the formed part ranging from surface streaks to severe bubbling. Pellets can be dried on trays in a circulating air oven or in desiccating hopper dryer. Drying conditions recommended are 4 hours at 300°F (149°C) .

## Injection Molding

AvaSpire AV-651 resins can be readily injection molded in most screw injection machines. A general purpose screw with a 2:1 to 3:1 compression ratio is recommended, as is minimum back pressure. Injection speeds should be as fast as possible, consistent with part appearance requirements. Mold temperatures in the range of 320°F to 375°F (160°C to 190°C) are suggested. Melt temperature should generally range from 690°F to 730°F (366°C to 388°C). Recommended barrel temperature settings are shown in the following table.

**Caution: Exceeding 780°F (415°C) during processing may cause degradation.**

Zone heater settings		
Zone	Recommended Barrel Temperatures	
	°F	°C
Rear (Feed)	670	354
Middle	690	365
Front	700	371
Nozzle	705	374

## Standard Packaging and Labeling

AvaSpire AV-651 resin is packaged in polyethylene buckets, cardboard boxes, or multiwall bags depending upon the order size.

Individual packages will be plainly marked with the product number, the color, the lot number, and the net weight.

## Product Safety and Emergency Service

For product safety information or a Material Safety Data Sheet on a product of Solvay Advanced Polymers

**1 (800) 621-4557**

**1 (770) 772-8880 outside of U.S.**

For information or help in an emergency such as a spill, leak, fire or explosion, call day or night:

Emergency Health Information

**1 (800) 621-4590**

**1 (770) 772-5177 outside of U.S.**

Emergency Spill Information

**CHEMTREC 1 (800) 424-9300**

**1 (703) 527-3887 outside of U.S.**

**collect calls accepted**

## For Additional Information

Technical Service

**1 (800) 621-4557**

Customer Service

**1 (800) 848-9744**

AvaSpire is a trademark of Solvay Advanced Polymers, L.L.C.

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Advanced Polymers, L.L.C. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Solvay Advanced Polymers, L.L.C. reserves the right to make additions, deletions, or modifications to the information at any time without prior notification.