

KetaSpire® KT-850

polyetheretherketone

KetaSpire® KT-850 is the intermediate-flow grade of unreinforced polyetheretherketone (PEEK) supplied in a natural-color pellet form. KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent wear resistance, best-in-class fatigue resistance, ease of melt processing, high purity and excellent chemical resistance to organics, acids and bases.

These properties make it well-suited for applications in healthcare, transportation, electronics, chemical processing and other industrial uses.

- Natural: KT-850 NT

General

Material Status	<ul style="list-style-type: none"> • Commercial: Active 	
Availability	<ul style="list-style-type: none"> • Africa & Middle East • Asia Pacific • Europe 	<ul style="list-style-type: none"> • Latin America • North America
Features	<ul style="list-style-type: none"> • Chemical Resistant • Ductile • Fatigue Resistant • Flame Retardant 	<ul style="list-style-type: none"> • Good Dimensional Stability • Good Impact Resistance • High Heat Resistance
Uses	<ul style="list-style-type: none"> • Aircraft Applications • Automotive Applications • Bearings • Bushings • Compounding • Electrical/Electronic Applications 	<ul style="list-style-type: none"> • Film • Industrial Applications • Medical/Healthcare Applications • Oil/Gas Applications • Seals • Tubing
RoHS Compliance	<ul style="list-style-type: none"> • RoHS Compliant 	
Appearance	<ul style="list-style-type: none"> • Natural Color 	
Forms	<ul style="list-style-type: none"> • Pellets 	
Processing Method	<ul style="list-style-type: none"> • Extrusion Blow Molding • Film Extrusion • Injection Molding • Machining 	<ul style="list-style-type: none"> • Profile Extrusion • Thermoforming • Wire & Cable Extrusion

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.30		ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage ¹			ASTM D955
Flow : 3.18 mm	1.2	%	
Across Flow : 3.18 mm	1.4	%	
Water Absorption (24 hr)	0.10	%	ASTM D570

Mechanical

	Typical Value	Unit	Test method
Tensile Modulus ²	3650	MPa	ASTM D638
Tensile Strength ²	96.5	MPa	ASTM D638

KetaSpire® KT-850

polyetheretherketone

Mechanical	Typical Value	Unit	Test method
Tensile Elongation			ASTM D638
Yield ²	5.2	%	
Break ³	> 50	%	
Break ²	20 to 30	%	
Flexural Modulus	3700	MPa	ASTM D790
Flexural Strength	146	MPa	ASTM D790
Impact	Typical Value	Unit	Test method
Notched Izod Impact	91	J/m	ASTM D256
Unnotched Izod Impact	No Break		ASTM D256
Hardness	Typical Value	Unit	Test method
Durometer Hardness (Shore D, 1 sec)	88		ASTM D2240
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Annealed	162	°C	
Glass Transition Temperature	150	°C	ASTM D3418
Melting Temperature	340	°C	ASTM D3418
CLTE - Flow (-50 to 50°C)	4.3E-5	cm/cm/°C	ASTM E831
Fill Analysis	Typical Value	Unit	Test method
Melt Viscosity (400°C, 1000 sec ⁻¹)	380	Pa·s	ASTM D3835

KetaSpire® KT-850

polyetheretherketone

Injection	Typical Value	Unit
Drying Temperature	150	°C
Drying Time	4.0	hr
Rear Temperature	355	°C
Middle Temperature	365	°C
Front Temperature	370	°C
Nozzle Temperature	375	°C
Mold Temperature	175 to 205	°C
Injection Rate	Fast	
Screw Compression Ratio	2.5:1.0 to 3.5:1.0	

Injection Notes

Back Pressure: minimum

Notes

Typical properties: these are not to be construed as specifications.

¹ 5" x 0.5" x 0.125" bar

² 51 mm/min

³ 5.1 mm/min



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.