

KetaSpire® KT-880 FW30

polyetheretherketone

KetaSpire® KT-880 FW30 is a polyetheretherketone (PEEK) compound with higher flow than KetaSpire® KT-820 SL30, making it more suitable for injection molding applications. It is designed to deliver a balance of excellent mechanical properties, wear resistance and low coefficient of friction in both dry and externally lubricated applications. The resin is formulated with anti-friction/anti-wear additive system comprised of carbon fiber and polytetrafluoroethylene (PTFE).

properties, which include excellent wear resistance, best-in-class fatigue resistance, ease of melt processing, high purity, and excellent chemical resistance to organics, acids, and bases.

These properties make it well-suited for applications in transportation, electronics, chemical processing, and industrial uses including oil and gas exploration and production. The resin is black in color in its natural state.

KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Carbon Fiber, 30% Filler by Weight	
Features	• Autoclave Sterilizable • Chemical Resistant • E-beam Sterilizable • Ethylene Oxide Sterilizable • Fatigue Resistant • Flame Retardant • Good Dimensional Stability • Good Sterilizability • Heat Sterilizable	• High Flow • High Heat Resistance • High Stiffness • High Strength • Radiation (Gamma) Resistant • Radiation Sterilizable • Steam Resistant • Steam Sterilizable
Uses	• Aircraft Applications • Connectors • Dental Applications • Electrical/Electronic Applications • Film • Hospital Goods • Industrial Applications	• Medical Devices • Medical/Healthcare Applications • Oil/Gas Applications • Pump Parts • Seals • Surgical Instruments
RoHS Compliance	• Contact Manufacturer	
Automotive Specifications	• GM GMW16841P-PEEK-CF15-PTFE15 Color: Natural	
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding • Machining	• Profile Extrusion

Physical	Typical Value Unit	Test method
Density	1.45 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (400°C/5.0 kg)	50 g/10 min	ASTM D1238

KetaSpire® KT-880 FW30

polyetheretherketone

Physical	Typical Value	Unit	Test method
Molding Shrinkage			ISO 294-4
Across Flow	0.55	%	
Flow	0.012	%	
PV Limit ¹	300000 to 400000	psi·fpm	
Mechanical	Typical Value	Unit	Test method
Tensile Modulus			
--	13500	MPa	ASTM D638
--	16000	MPa	ISO 527-2
Tensile Stress			
Break	180	MPa	ISO 527-2
--	194	MPa	ASTM D638
Tensile Elongation			
Break	1.8	%	ASTM D638
Break	1.7	%	ISO 527-2
Flexural Modulus			
--	13500	MPa	ASTM D790
--	13200	MPa	ISO 178
Flexural Strength			
--	280	MPa	ASTM D790
--	260	MPa	ISO 178
Compressive Strength	138	MPa	ASTM D695
Shear Strength	83.0	MPa	ASTM D732
Coefficient of Friction ²	0.28		ASTM D3702
Wear Factor (0.22 MPa, 4.1 m/sec)	46	10 ⁻⁸ mm ³ /N·m	ASTM D3702
Impact	Typical Value	Unit	Test method
Notched Izod Impact			
--	68	J/m	ASTM D256
--	7.0	kJ/m ²	ISO 180
Unnotched Izod Impact	530	J/m	ASTM D4812
Hardness	Typical Value	Unit	Test method
Rockwell Hardness	99		ASTM D785
Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	147	°C	ISO 11357-2
Melting Temperature	343	°C	ISO 11357-3
Fill Analysis	Typical Value	Unit	Test method
Melt Viscosity (400°C, 1000 sec ⁻¹)	150	Pa·s	ASTM D3835
Injection	Typical Value	Unit	Test method
Drying Temperature	150	°C	
Drying Time	4.0	hr	
Rear Temperature	365	°C	
Middle Temperature	370	°C	
Front Temperature	375	°C	

KetaSpire® KT-880 FW30

polyetheretherketone

Injection	Typical Value	Unit
Nozzle Temperature	380	°C
Mold Temperature	175 to 205	°C
Injection Rate	Fast	
Screw Compression Ratio	2.5:1.0 to 3.5:1.0	

Notes

Typical properties: these are not to be construed as specifications.

¹ GMW 16771-Sequence B

² Dry



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.