

KetaSpire® KT-880 GF15

polyetheretherketone

KetaSpire® KT-880 GF15 is a high flow, 15% glass-fiber reinforced grade of polyetheretherketone (PEEK). This resin offers higher strength and stiffness properties relative to unreinforced KetaSpire® PEEK resin. The glass fiber content is optimized to provide a balance of strength and stiffness with toughness-related properties, such as impact resistance and elongation at break. The low fiberglass loading gives the resin improved surface aesthetics and reduced anisotropy over comparable 30% glass reinforced formulations.

KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of

properties, which include excellent wear resistance, best-in-class fatigue resistance, ease of melt processing, high purity and excellent chemical resistance to organics, acids and bases.

These properties make it well-suited for applications in oil & gas, healthcare, transportation, electronics, chemical processing and other industrial uses.

- Natural: KT-880 GF15 NT

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight	
Features	<ul style="list-style-type: none"> • Autoclave Sterilizable • Biocompatible • Chemical Resistant • E-beam Sterilizable • Ethylene Oxide Sterilizable • Fatigue Resistant • Flame Retardant • Good Dimensional Stability • Good Sterilizability • Heat Sterilizable 	<ul style="list-style-type: none"> • High Flow • High Heat Resistance • High Stiffness • High Strength • Radiation (Gamma) Resistant • Radiation Sterilizable • Radiotranslucent • Steam Resistant • Steam Sterilizable
Uses	<ul style="list-style-type: none"> • Aircraft Applications • Automotive Applications • Connectors • Dental Applications • Electrical/Electronic Applications • Film • Hospital Goods 	<ul style="list-style-type: none"> • Industrial Applications • Medical Devices • Medical/Healthcare Applications • Oil/Gas Applications • Pump Parts • Seals • Surgical Instruments
RoHS Compliance	• Contact Manufacturer	
Appearance	• Tan	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.42		ASTM D792
Ash Content	15	%	ISO 3451-1

KetaSpire® KT-880 GF15

polyetheretherketone

Mechanical	Typical Value	Unit	Test method
Tensile Modulus	6700	MPa	ASTM D638
Tensile Stress (Break)	138	MPa	ASTM D638
Tensile Strain ¹ (Break)	5.0	%	ASTM D638
Flexural Stress	231	MPa	ASTM D638
Modulus of Elasticity	6.61	GPa	ASTM D638

Impact	Typical Value	Unit	Test method
Charpy Unnotched Impact Strength	53	kJ/m ²	ISO 179
Notched Izod Impact			
--	47	J/m	ASTM D256
--	5.0	kJ/m ²	ISO 180
Unnotched Izod Impact	660	J/m	ASTM D256

Thermal	Typical Value	Unit	Test method
Heat Deflection Temperature 1.8 MPa, Unannealed	278	°C	ASTM D648

Injection	Typical Value	Unit
Drying Temperature	150	°C
Drying Time	4.0	hr
Rear Temperature	365	°C
Middle Temperature	371	°C
Front Temperature	377	°C
Nozzle Temperature	382	°C
Mold Temperature	177 to 204	°C
Injection Rate	Fast	
Screw Compression Ratio	2.5:1.0 to 3.5:1.0	

Notes

Typical properties: these are not to be construed as specifications.

¹ Type 1A, 5 mm/min



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.