

KetaSpire® KT-880 GF20

polyetheretherketone

KetaSpire® KT-880 GF20 is a high flow, 20% glass-fiber reinforced grade of polyetheretherketone (PEEK). This resin offers higher strength and stiffness properties relative to unreinforced KetaSpire® PEEK resin. The glass fiber content is optimized to provide a balance of strength and stiffness with toughness-related properties, such as impact resistance and elongation at break. This level of reinforcement also affords greater mechanical robustness in structural applications, particularly those with service temperatures approaching 240°C (464°F).

KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent wear resistance, best-in-class fatigue resistance, ease of melt processing, high purity and excellent chemical resistance to organics, acids and bases.

These properties make it well-suited for applications in healthcare, transportation, electronics, chemical processing and other industrial uses.

General

Material Status	<ul style="list-style-type: none"> Commercial: Active 	
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific Europe 	<ul style="list-style-type: none"> Latin America North America
Filler / Reinforcement	<ul style="list-style-type: none"> Glass Fiber, 20% Filler by Weight 	
Features	<ul style="list-style-type: none"> Autoclave Sterilizable Biocompatible Chemical Resistant E-beam Sterilizable Ethylene Oxide Sterilizable Fatigue Resistant Flame Retardant Good Dimensional Stability Good Sterilizability Heat Sterilizable 	<ul style="list-style-type: none"> High Flow High Heat Resistance High Stiffness High Strength Radiation (Gamma) Resistant Radiation Sterilizable Radioopaque Steam Resistant Steam Sterilizable
Uses	<ul style="list-style-type: none"> Aircraft Applications Automotive Applications Connectors Dental Applications Electrical/Electronic Applications Film Hospital Goods 	<ul style="list-style-type: none"> Industrial Applications Medical Devices Medical/Healthcare Applications Oil/Gas Applications Pump Parts Seals Surgical Instruments
Agency Ratings	<ul style="list-style-type: none"> MIL P-46183 Type II Class 2 	
RoHS Compliance	<ul style="list-style-type: none"> Contact Manufacturer 	
Appearance	<ul style="list-style-type: none"> Tan 	
Forms	<ul style="list-style-type: none"> Pellets 	
Processing Method	<ul style="list-style-type: none"> Injection Molding 	

Physical

	Typical Value	Unit	Test method
Density	1.46	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	18	g/10 min	ASTM D1238
Water Absorption (24 hr)	0.022	%	ISO 15512
Ash Content	20	%	ISO 3451-1

KetaSpire® KT-880 GF20

polyetheretherketone

Mechanical	Typical Value	Unit	Test method
Tensile Modulus			
--	8200	MPa	ASTM D638
--	8300	MPa	ISO 527-2
Tensile Strength			
Break	152	MPa	ASTM D638
Break	162	MPa	ISO 527-2
Tensile Elongation			
Break	3.7	%	ASTM D638
Break	3.5	%	ISO 527-2/1A/5
Flexural Modulus			
--	7860	MPa	ASTM D790
--	7720	MPa	ISO 178
Flexural Strength			
--	254	MPa	ASTM D790
--	238	MPa	ISO 178
Modulus of Elasticity			
--	8.24	GPa	ISO 527
--	8.34	GPa	ASTM D638
Impact	Typical Value	Unit	Test method
Charpy Unnotched Impact Strength	60	kJ/m ²	ISO 179
Notched Izod Impact			
--	60	J/m	ASTM D256
--	6.0	kJ/m ²	ISO 180
Unnotched Izod Impact	770	J/m	ASTM D256
Hardness	Typical Value	Unit	Test method
Rockwell Hardness (M-Scale)	103		ASTM D785
Thermal	Typical Value	Unit	Test method
Melting Temperature ¹	345	°C	ISO 11357
Electrical	Typical Value	Unit	Test method
Surface Resistivity	5.0E+15	ohms	ASTM D257
Volume Resistivity	7.0E+15	ohms·cm	ASTM D257
Dielectric Strength	310	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	3.34		
1 kHz	3.35		
1 MHz	3.35		
Dissipation Factor			ASTM D150
60 Hz	2.0E-3		
1 kHz	1.0E-3		
1 MHz	4.0E-3		
Fill Analysis	Typical Value	Unit	Test method
Melt Viscosity (400°C, 1000 sec ⁻¹)	280	Pa·s	ASTM D3835

KetaSpire® KT-880 GF20

polyetheretherketone

Injection	Typical Value	Unit
Drying Temperature	150	°C
Drying Time	4.0	hr
Rear Temperature	365	°C
Middle Temperature	371	°C
Front Temperature	377	°C
Nozzle Temperature	382	°C
Mold Temperature	177 to 204	°C
Injection Rate	Fast	
Screw Compression Ratio	2.5:1.0 to 3.5:1.0	

Notes

Typical properties: these are not to be construed as specifications.

¹ DSC First heat



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.